

TEST REPORT

Test Report # 16H-07991 Date of Report Issue: December 1, 2016
Date of Sample Received: November 24, 2016 Pages: Page 1 of 10

CLIENT INFORMATION:

Company: Hit Promotional Products
Recipient: Nathan Cotter
Recipient Email: ncotter@hitpromo.net



SAMPLE INFORMATION:

Description:	15oz. Metallic Banded Tumbler	Purchase Order Number:	188685
Assortment:	3 colors	Agent:	Growth-Sonic
SKU No.:	5788	Country of Origin:	China
Factory No.:	127740	Labeled Age Grade:	-
Country of Distribution:	United States	Recommended Age Grade:	-
Quantity Submitted:	5 pcs per style	Tested Age Grade:	-
Testing Period:	11/24/2016 – 12/01/2016		

OVERALL RESULT:

 **PASS**

Refer to page 2 for test result summary and appropriate notes.

ANSECO GROUP (HK) LIMITED



Vincent Chow Wai Kit
Manager, Chemical Laboratory

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street • Kwun Tong • Kowloon • Hong Kong • Tel: (852)3185 8000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

TEST RESULTS SUMMARY:

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	CPSIA Section 101 & 16 CFR 1303, Total Lead in Paints and Surface Coatings
PASS	CPSIA Section 101, Total Lead in Substrate Materials
PASS	Client's Requirement, Bisphenol A and Bisphenol S [#]
PASS	FDA 21 CFR 177.1210, Closures with Sealing Gaskets [#]
PASS	FDA 21 CFR 177.1520, Polypropylene Homopolymers
PASS	Canadian Consumer Products Containing Lead (Contact with Mouth) Regulation SOR/2010-273 as Amended by SOR/2016-171, Total Lead in Accessible Substrates

DETAILED RESULTS:

CPSIA Section 101 & 16 CFR 1303, Total Lead in Paints and Surface Coatings

Test Method: CPSC-CH-E-1003-09.1
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1	2+3+4	---	---	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	---	---	---	90
Conclusion	PASS	PASS	---	---	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

DETAILED RESULTS:

CPSIA Section 101, Total Lead in Substrate Materials

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	5	7	8	---	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	---	---	100
Conclusion	PASS	PASS	PASS	---	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

DETAILED RESULTS:

Client's Requirement, Bisphenol A and Bisphenol S

Test Method: AI | ANSECO Method#
 Analytical Method: Liquid Chromatography with Mass Spectrometry

Specimen No.		6	7	---	---	Limit (ppb)
Test Item	CAS No.	Result (ppb)	Result (ppb)	Result (ppb)	Result (ppb)	
Bisphenol A (BPA)	80-05-7	ND	ND	---	---	ND
Bisphenol S (BPS)	80-09-1	ND	ND	---	---	ND
Conclusion		PASS	PASS	---	---	

Note:

ppb (Parts per billion) = µg/kg (Micrograms per kilogram)

LT = Less than

ND = Not detected (Reporting limit: BPA = 1000 ppb; BPS = 200 ppb)

DETAILED RESULTS:

FDA 21 CFR 177.1210, Closures with Sealing Gaskets

Test Method: FDA 21 CFR 177.1210[#]

Specimen No.			7	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (ppm)	Fill boiling, cool to 100°F	75 minutes	ND	10	50
Conclusion			PASS		

Note:

Temp. = Temperature

°F = Degree Fahrenheit

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1210 Table 2 Section 2.

DETAILED RESULTS:

FDA 21 CFR 177.1520, Polypropylene Homopolymers

Test Method: FDA 21 CFR 177.1520

Specimen No.			6	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.894	NA	0.880 – 0.913
Melting point (°C)	NA	NA	165.3	NA	150 – 180
n-Hexane extractive (% w/w)	Reflux	2 hours	1.8	0.1	6.4
Xylene extractive (% w/w)	25°C	1 hour	2.0	0.5	9.8
Conclusion			PASS		

Note:

Temp. = Temperature

°C = Degree Celsius

g/cc = Grams per cubic centimeter

% w/w = Percent by weight

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1520 (c) 1.1.

DETAILED RESULTS:

Canadian Consumer Products Containing Lead (Contact with Mouth) Regulation SOR/2010-273 as Amended by SOR/2016-171, Total Lead in Accessible Substrates

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	5	7	8	---	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	---	---	90
Conclusion	PASS	PASS	PASS	---	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
1	Silvery coating	On rim/ bottom (all styles)
2	Red coating	On main body (red style)
3	Blue coating	On main body (blue style)
4	Green coating	On main body (green style)
5	Grey plastic	Lid/ inner wall/ slider/ bottom (all styles)
6	Grey plastic (PP-homo)	Lid/ inner wall/ slider (all styles)
7	Translucent soft plastic	Gasket (all styles)
8	Silvery metal	Main body/ ring of lid (all styles)

SAMPLE PHOTO:



-End Report-