



# TEST REPORT

Test Report # 17H-003026 Date of Report Issue: May 5, 2017  
 Date of Sample Received: April 25, 2017 Pages: Page 1 of 11

## CLIENT INFORMATION:

Company: Hit Promotional Products  
 Recipient: Nathan Cotter  
 Recipient Email: ncotter@hitpromo.net



## SAMPLE INFORMATION:

Description:	16oz. Resort Tumbler	Purchase Order Number:	202725
Assortment:	4 colors	Agent:	Brand New Days
SKU No.:	5873	Country of Origin:	China
Factory No.:	106712	Labeled Age Grade:	-
Country of Distribution:	United States	Recommended Age Grade:	-
Quantity Submitted:	6 pcs (Orange, Blue, Purple), 5 pcs (Green) + 1 lot Parts	Tested Age Grade:	-
Testing Period:	04/25/2017 – 05/05/2017		

## OVERALL RESULT:

**PASS**

Refer to page 2 for test result summary and appropriate notes.

ANSECO GROUP (HK) LIMITED

Loska Yeung Lok Ka  
 Assistant Manager, Chemical Laboratory

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street • Kwun Tong • Kowloon • Hong Kong • Tel: (852)3185 8000

*The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.*

*The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.*

*This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.*

*ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.*

**TEST RESULTS SUMMARY:**

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	CPSIA Section 101, Total Lead in Substrate Materials
PASS	Client's Requirement, Bisphenol A and Bisphenol S <sup>#</sup>
PASS	FDA 21 CFR 177.1210, Closures with Sealing Gaskets <sup>#</sup>
PASS	FDA 21 CFR 177.1520, Polypropylene Homopolymers
PASS	FDA 21 CFR 180.22 and 181.32, Acrylonitrile/Styrene Copolymers
PASS	Canadian Consumer Products Containing Lead (Contact with Mouth) Regulation SOR/2010-273 as Amended by SOR/2016-171, Total Lead in Accessible Substrates

*Remark:*

CPSIA Section 101 & 16 CFR 1303, Total Lead in Paints and Surface Coatings was not conducted as no paint and similar surface coating found on received sample.

**DETAILED RESULTS:****CPSIA Section 101, Total Lead in Substrate Materials**

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2+3	4+5+6	7	---	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	---	---	<b>100</b>
<b>Conclusion</b>	PASS	PASS	PASS	---	---	

*Note:*

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:****Client's Requirement, Bisphenol A and Bisphenol S**Test Method: AI|ANSECO Method<sup>#</sup>

Analytical Method: Liquid Chromatography with Mass Spectrometry

Specimen No.		1	3	4	5	Limit (ppb)
Test Item	CAS No.	Result (ppb)	Result (ppb)	Result (ppb)	Result (ppb)	
Bisphenol A (BPA)	80-05-7	ND	ND	ND	ND	ND
Bisphenol S (BPS)	80-09-1	ND	ND	ND	ND	ND
<b>Conclusion</b>		PASS	PASS	PASS	PASS	

Specimen No.		6	7	---	---	Limit (ppb)
Test Item	CAS No.	Result (ppb)	Result (ppb)	Result (ppb)	Result (ppb)	
Bisphenol A (BPA)	80-05-7	ND	ND	---	---	ND
Bisphenol S (BPS)	80-09-1	ND	ND	---	---	ND
<b>Conclusion</b>		PASS	PASS	---	---	

*Note:*

ppb (Parts per billion) = µg/kg (Micrograms per kilogram)

NA = Not applicable

LT = Less than

ND = Not detected (Reporting limit: BPA = 1000 ppb; BPS = 200 ppb)



**DETAILED RESULTS:**

**FDA 21 CFR 177.1210, Closures with Sealing Gaskets**

Test Method: FDA 21 CFR 177.1210<sup>#</sup>

Specimen No.			7	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (ppm)	Fill boiling, cool to 100°F	100 minutes	ND	10	50
<b>Conclusion</b>			PASS		

*Note:*

Temp. = Temperature

°F = Degree Fahrenheit

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

*Remark:*

The specification is quoted from 21 CFR 177.1210 Table 2 Section 2.

**DETAILED RESULTS:****FDA 21 CFR 177.1520, Polypropylene Homopolymers**

Test Method: FDA 21 CFR 177.1520

Specimen No.		1		Result	RL	Limit
Test Item	Test Condition					
	Temp.	Duration				
Density (g/cc)	NA	NA	0.904	NA	0.880 – 0.913	
Melting point (°C)	NA	NA	164.2	NA	150 – 180	
n-Hexane extractive (% w/w)	Reflux	2 hours	1.2	0.1	6.4	
Xylene extractive (% w/w)	25°C	1 hour	1.4	0.5	9.8	
<b>Conclusion</b>			PASS			

**Note:**

Temp. = Temperature

°C = Degree Celsius

g/cc = Grams per cubic centimeter

% w/w = Percent by weight

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

**Remark:**

The specification is quoted from 21 CFR 177.1520 (c) 1.1.

**DETAILED RESULTS:****FDA 21 CFR 180.22 and 181.32, Acrylonitrile/Styrene Copolymers**

Test Method: FDA 21 CFR 180.22 and 181.32

Analytical Method: Headspace-Gas Chromatography with Mass Spectrometry

Acrylonitrile Monomers:

Specimen No.			3	RL	Limit
Test Simulant	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in <sup>2</sup> )	120°F	2 hours	ND	<b>0.001</b>	<b>0.003</b>
3% Acetic acid extractive (mg/in <sup>2</sup> )	120°F	2 hours	ND	<b>0.001</b>	<b>0.003</b>
<b>Conclusion</b>			PASS		

Specimen No.			4	RL	Limit
Test Simulant	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in <sup>2</sup> )	120°F	2 hours	ND	<b>0.001</b>	<b>0.003</b>
3% Acetic acid extractive (mg/in <sup>2</sup> )	120°F	2 hours	ND	<b>0.001</b>	<b>0.003</b>
<b>Conclusion</b>			PASS		

*Note:*

Temp. = Temperature

°F = Degree Fahrenheit

mg/in<sup>2</sup> = Milligrams per square inch

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

*Remark:*

The specification is quoted from 21 CFR 181.32 (b) (3).

**DETAILED RESULTS:****FDA 21 CFR 180.22 and 181.32, Acrylonitrile/Styrene Copolymers**

Test Method: FDA 21 CFR 180.22 and 181.32

Analytical Method: Headspace-Gas Chromatography with Mass Spectrometry

Acrylonitrile Monomers:

Specimen No.			5	RL	Limit
Test Simulant	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in <sup>2</sup> )	120°F	2 hours	ND	<b>0.001</b>	<b>0.003</b>
3% Acetic acid extractive (mg/in <sup>2</sup> )	120°F	2 hours	ND	<b>0.001</b>	<b>0.003</b>
<b>Conclusion</b>			PASS		

Specimen No.			6	RL	Limit
Test Simulant	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in <sup>2</sup> )	120°F	2 hours	ND	<b>0.001</b>	<b>0.003</b>
3% Acetic acid extractive (mg/in <sup>2</sup> )	120°F	2 hours	ND	<b>0.001</b>	<b>0.003</b>
<b>Conclusion</b>			PASS		

*Note:*

Temp. = Temperature

°F = Degree Fahrenheit

mg/in<sup>2</sup> = Milligrams per square inch

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

*Remark:*

The specification is quoted from 21 CFR 181.32 (b) (3).



**DETAILED RESULTS:****Canadian Consumer Products Containing Lead (Contact with Mouth) Regulation SOR/2010-273 as Amended by SOR/2016-171, Total Lead in Accessible Substrates**

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)  
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2+3	4+5+6	7	---	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	---	---	<b>90</b>
<b>Conclusion</b>	PASS	PASS	PASS	---	---	

*Note:*

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**SPECIMEN DESCRIPTION:**

Specimen No.	Specimen Description	Location
1	White plastic (PP-homo)	Lid/ slider (all styles)
2	Transparent plastic	Outer wall (all styles)
3	Green plastic (AS)	Inner wall (green style)
4	Orange plastic (AS)	Inner wall (orange style)
5	Blue plastic (AS)	Inner wall (blue style)
6	Purple plastic (AS)	Inner wall (purple style)
7	Translucent soft plastic (Silicone)	Gasket (all styles)

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street • Kwun Tong • Kowloon • Hong Kong • Tel: (852)3185 8000

*The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.*

*The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.*

*This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.*

*ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.*



**SAMPLE PHOTO:**



-End Report-