

TEST REPORT

Test Report # 16H-06561 Date of Report Issue: October 13, 2016
Date of Sample Received: October 4, 2016 Pages: Page 1 of 13

CLIENT INFORMATION:

Company: Hit Promotional Products
Recipient: Nathan Cotter
Recipient Email: ncotter@hitpromo.net



SAMPLE INFORMATION:

Description:	24oz. Fresh Fusion Bottle	Purchase Order Number:	181761
Assortment:	5 colors	Agent:	Growth-Sonic
SKU No.:	5976	Country of Origin:	China
Factory No.:	127894	Labeled Age Grade:	-
Country of Distribution:	United States	Recommended Age Grade:	-
Quantity Submitted:	5 pcs per style	Tested Age Grade:	-
Testing Period:	10/04/2016 – 10/13/2016		

OVERALL RESULT:



Refer to page 2 for test result summary and appropriate notes.

ANSECO GROUP (HK) LIMITED



Vincent Chow Wai Kit
Manager, Chemical Laboratory

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street • Kwun Tong • Kowloon • Hong Kong • Tel: (852)3185 8000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

TEST RESULTS SUMMARY:

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	CPSIA Section 101, Total Lead in Substrate Materials
PASS	Client’s Requirement, Bisphenol A and Bisphenol S [#]
PASS	FDA 21 CFR 177.1210, Closures with Sealing Gaskets [#]
PASS	FDA 21 CFR 177.1520, Polypropylene Copolymers
PASS	FDA 21 CFR 177.1630, Polyethylene Phthalate Polymers
PASS	FDA 21 CFR 180.22 and 181.32, Acrylonitrile/Styrene Copolymers
PASS	Canadian Consumer Products Containing Lead (Contact with Mouth) Regulation SOR/2010-273 as Amended by SOR/2016-171, Total Lead in Accessible Substrates

Remark:

CPSIA Section 101 & 16 CFR 1303, Total Lead in Paints and Surface Coatings and Canadian Surface Coating Materials Regulations (SOR/2016-193), Total Lead and Mercury in Paints and Surface Coatings were not conducted as no paint and similar surface coating found on received sample.

DETAILED RESULTS:

CPSIA Section 101, Total Lead in Substrate Materials

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2	3+4+5	6+7	8+9	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	---	100
Conclusion	PASS	PASS	PASS	PASS	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

DETAILED RESULTS:

Client’s Requirement, Bisphenol A and Bisphenol S

Test Method: AI | ANSECO Method[#]

Analytical Method: Liquid Chromatography with Mass Spectrometry

Specimen No.		2	3	4	5	Limit (ppb)
Test Item	CAS No.	Result (ppb)	Result (ppb)	Result (ppb)	Result (ppb)	
Bisphenol A (BPA)	80-05-7	ND	ND	ND	ND	ND
Bisphenol S (BPS)	80-09-1	ND	ND	ND	ND	ND
Conclusion		PASS	PASS	PASS	PASS	

Specimen No.		6	7	8	9	Limit (ppb)
Test Item	CAS No.	Result (ppb)	Result (ppb)	Result (ppb)	Result (ppb)	
Bisphenol A (BPA)	80-05-7	ND	ND	ND	ND	ND
Bisphenol S (BPS)	80-09-1	ND	ND	ND	ND	ND
Conclusion		PASS	PASS	PASS	PASS	

Note:

ppb (Parts per billion) = µg/kg (Micrograms per kilogram)

LT = Less than

ND = Not detected (Reporting limit: BPA = 1000 ppb; BPS = 200 ppb)

DETAILED RESULTS:

FDA 21 CFR 177.1210, Closures with Sealing Gaskets

Test Method: FDA 21 CFR 177.1210[#]

Specimen No.			2	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (ppm)	Fill boiling, cool to 100°F	120 minutes	ND	10	50
Conclusion			PASS		

Note:

Temp. = Temperature

°F = Degree Fahrenheit

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1210 Table 2 Section 2.

DETAILED RESULTS:

FDA 21 CFR 177.1520, Polypropylene Copolymers

Test Method: FDA 21 CFR 177.1520

Specimen No.			3	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.904	NA	0.85 – 1.00
n-Hexane extractive (% w/w)	50 °C	2 hours	0.5	0.4	5.5
Xylene extractive (% w/w)	25 °C	1 hour	ND	1	30
Conclusion			PASS		

Specimen No.			4	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.904	NA	0.85 – 1.00
n-Hexane extractive (% w/w)	50 °C	2 hours	ND	0.4	5.5
Xylene extractive (% w/w)	25 °C	1 hour	ND	1	30
Conclusion			PASS		

Note:

Temp. = Temperature

°C = Degree Celsius

g/cc = Grams per cubic centimeter

% w/w = Percent by weight

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1520 (c) 3.1a.

DETAILED RESULTS:

FDA 21 CFR 177.1520, Polypropylene Copolymers

Test Method: FDA 21 CFR 177.1520

Specimen No.			5	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.902	NA	0.85 – 1.00
n-Hexane extractive (% w/w)	50 °C	2 hours	ND	0.4	5.5
Xylene extractive (% w/w)	25 °C	1 hour	1.3	1	30
Conclusion			PASS		

Specimen No.			6	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.904	NA	0.85 – 1.00
n-Hexane extractive (% w/w)	50 °C	2 hours	0.4	0.4	5.5
Xylene extractive (% w/w)	25 °C	1 hour	ND	1	30
Conclusion			PASS		

Note:

Temp. = Temperature

°C = Degree Celsius

g/cc = Grams per cubic centimeter

% w/w = Percent by weight

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1520 (c) 3.1a.

DETAILED RESULTS:

FDA 21 CFR 177.1520, Polypropylene Copolymers

Test Method: FDA 21 CFR 177.1520

Specimen No.			7	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.902	NA	0.85 – 1.00
n-Hexane extractive (% w/w)	50 °C	2 hours	ND	0.4	5.5
Xylene extractive (% w/w)	25 °C	1 hour	1.2	1	30
Conclusion			PASS		

Note:

Temp. = Temperature

°C = Degree Celsius

g/cc = Grams per cubic centimeter

% w/w = Percent by weight

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1520 (c) 3.1a.

DETAILED RESULTS:

FDA 21 CFR 177.1630, Polyethylene Phthalate Polymers

Test Method: FDA 21 CFR 177.1630

Specimen No.			9	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in ²)	250	2 hours	ND	0.1	0.5
n-Heptane extractive (mg/in ²)	150	2 hours	ND	0.1	0.5
Conclusion			PASS		

Note:

Temp. = Temperature

°F = Degree Fahrenheit

mg/in² = Milligrams per square inch

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1630 (f).

DETAILED RESULTS:

FDA 21 CFR 180.22 and 181.32, Acrylonitrile/Styrene Copolymers

Test Method: FDA 21 CFR 180.22 and 181.32
 Analytical Method: Headspace-Gas Chromatography with Mass Spectrometry

Acrylonitrile Monomers:

Specimen No.			8	RL	Limit
Test Simulant	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in ²)	120°F	2 hours	ND	0.001	0.003
3% Acetic acid extractive (mg/in ²)	120°F	2 hours	ND	0.001	0.003
Conclusion			PASS		

Note:

Temp. = Temperature
 °F = Degree Fahrenheit
 mg/in² = Milligrams per square inch
 LT = Less than
 ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 181.32 (b) (3).

DETAILED RESULTS:

Canadian Consumer Products Containing Lead (Contact with Mouth) Regulation SOR/2010-273 as Amended by SOR/2016-171, Total Lead in Accessible Substrates

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2	3+4+5	6+7	8+9	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	---	90
Conclusion	PASS	PASS	PASS	PASS	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
1	White soft plastic	Handle of lid (all styles)
2	Translucent soft plastic	Gasket (all styles)
3	Red plastic (PP-co)	Lid/ bottom (red style)
4	Orange plastic (PP-co)	Lid/ bottom (orange style)
5	Yellow plastic (PP-co)	Lid/ bottom (yellow style)
6	Green plastic (PP-co)	Lid/ bottom (green style)
7	Blue plastic (PP-co)	Lid/ bottom (blue style)
8	Transparent plastic (AS)	Infuser (all styles)
9	Clear plastic (Tritan)	Body (all styles)

SAMPLE PHOTO:



-End Report-