





# **TEST REPORT**

Test Report # 18H-009462 Date of Report Issue: January 7, 2019

Date of Sample Received: December 7, 2018 Pages: Page 1 of 13

**CLIENT INFORMATION:** 

Company: Hit Promotional Products

Recipient: Nathan Cotter

Recipient Email: ncotter@hitpromo.net

**SAMPLE INFORMATION:** 

Description: 25oz. Double Wall Stainless Steel Bottle

Assortment: 3 colors Purchase Order Number: 290480

SKU No.: 5315 Agent: Headwind (Chairs,

Bottles)

Factory No.: 129930 Country of Origin: China

Country of Distribution: United States Labeled Age Grade: -

Quantity Submitted: 2 pcs per style + 2 lots

**Parts** 

Testing Period: 12/07/2018 – 12/18/2018

12/31/2018 - 01/07/2019

Recommended Age Grade: -

Tested Age Grade:

**OVERALL RESULT:** 

**PASS** 

Refer to page 2 for test result summary and appropriate notes.

QIMA Testing (HK) Limited



Loska Yeung Lok Ka Assistant Manager, Chemical Laboratory

QIMA Testing (HK) Limited • 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong • Tel: (852)3185 8000.

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.



Test Report #: 18H-009462 Page 2 of 13

### **TEST RESULTS SUMMARY:**

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED			
PASS	CPSIA Section 101 & 16 CFR 1303, Total Lead in Paints and Surface Coatings			
PASS	California Proposition 65, Total Lead in Paints and Surface Coatings			
PASS	CPSIA Section 101, Total Lead in Substrate Materials			
PASS	California Proposition 65, Total Lead in Substrate Materials			
PASS	FDA GRAS Specifications, Total Chromium in Stainless Steel Food Containers#			
PASS	Client's Requirement, Bisphenol A and Bisphenol S#			
PASS	FDA 21 CFR 177.1210, Closures with Sealing Gaskets#			
PASS	FDA 21 CFR 177.1520, Polypropylene Homopolymers			
PASS	Canadian Consumer Products Containing Lead Regulations (SOR/2018-83), Total Lead Content			

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 18H-009462 Page 3 of 13

#### **DETAILED RESULTS:**

### CPSIA Section 101 & 16 CFR 1303, Total Lead in Paints and Surface Coatings

Test Method: CPSC-CH-E-1003-09.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2	3				Total
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Total Lead (Pb)	ND	ND				90
Conclusion	PASS	PASS				

#### Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Ver.12

CS-HK-RE005-HITP



Test Report #: 18H-009462 Page 4 of 13

### **DETAILED RESULTS:**

### California Proposition 65, Total Lead in Paints and Surface Coatings

Test Method: CPSC-CH-E-1003-09.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2	3				Total
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Total Lead (Pb)	ND	ND				90
Conclusion	PASS	PASS				

#### Note

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

### Remark:

The specification is quoted from client's requirement.

Ver.12



Test Report #: 18H-009462 Page 5 of 13

### **DETAILED RESULTS:**

### **CPSIA Section 101, Total Lead in Substrate Materials**

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal) Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	4	5	6	7	8	Total
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
Total Lead (Pb)	ND	ND	ND	ND	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

#### Note

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.



Test Report #: 18H-009462 Page 6 of 13

### **DETAILED RESULTS:**

### California Proposition 65, Total Lead in Substrate Materials

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal) Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	4	5	6	7	8	Total
Test Item	Result	Result	Result	Result	Result	Limit
rest item	(ppm)	(ppm)	(ppm)	(ppm)	(ppm)	(ppm)
Total Lead (Pb)	ND	ND	ND	ND	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

#### Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

### Remark:

The specification is quoted from client's requirement.



Test Report #: 18H-009462 Page 7 of 13

### **DETAILED RESULTS:**

### FDA GRAS Specifications, Total Chromium in Stainless Steel Food Containers

Test Method: In-House Method#

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	7					
Test Item	Result	Result	Result	Result	Result	Limit
rest item	(% m/m)					
Total Chromium (Cr)	17.9					GT 16
Conclusion	PASS					

Note:

% m/m = Percent by mass

GT = Greater than

## Remark:

The limit is quoted from ANSI/NSF 51-1997 Section 7.1.2.



Test Report #: 18H-009462 Page 8 of 13

### **DETAILED RESULTS:**

### Client's Requirement, Bisphenol A and Bisphenol S

Test Method: In-House Method<sup>#</sup>

Analytical Method: Liquid Chromatography with Mass Spectrometry or

Liquid Chromatography with Mass Spectrometry Mass Spectrometry

Specimen	No.	4	5			
Test Item	CAS No.	Result	Result	Result	Result	Limit
		(ppb)	(ppb)	(ppb)	(ppb)	(ppb)
Bisphenol A (BPA)	80-05-7	ND	ND			ND
Bisphenol S (BPS)	80-09-1	ND	ND			ND
Conclusi	ion	PASS	PASS			

Note

ppb (Parts per billion) = μg/kg (Micrograms per kilogram)

NA = Not applicable

LT = Less than

ND = Not detected (Reporting limit: BPA = 1000 ppb; BPS = 200 ppb)

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 18H-009462 Page 9 of 13

### **DETAILED RESULTS:**

### FDA 21 CFR 177.1210, Closures with Sealing Gaskets

Test Method: FDA 21 CFR 177.1210#

Specime	5					
Tost Itom	Test Co	ndition	Result	Result	RL	Limit
Test Item	Temp.	Duration	(ppm)	(ppm)	(ppm)	(ppm)
Distilled water extractive	Fill boiling Until Cool to 100°F		ND		10	50
		Conclusion	PASS			

### Note:

Temp. = Temperature

°F = Degree Fahrenheit

ppm (Parts per million) = mg/kg (Milligrams per kilogram foodstuff)

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

### Remark:

The specification is quoted from 21 CFR 177.1210 Table 2 Section 2.

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 18H-009462 Page 10 of 13

### **DETAILED RESULTS:**

### FDA 21 CFR 177.1520, Polypropylene Homopolymers

Test Method: FDA 21 CFR 177.1520

Specimen No.			4			
Test Item	Temp.	Duration	Result	Result	RL	Limit
Density (g/cc)	NA	NA	0.906		NA	0.880 - 0.913
Melting point (°C)	NA	NA	171.2		NA	150 – 180
n-Hexane extractive (%)	Reflux	2 hours	1.7		0.1	6.4
Xylene extractive (%)	120°C	2 hours or until total dissolved	3.9		0.5	9.8
		Conclusion	PASS			

#### Note:

Temp. = Temperature

°C = Degree Celsius

g/cc = Grams per cubic centimeter

% w/w = Percent by weight

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

#### Remark:

The specification is quoted from 21 CFR 177.1520 (c) 1.1.

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 18H-009462 Page 11 of 13

### **DETAILED RESULTS:**

### Canadian Consumer Products Containing Lead Regulations (SOR/2018-83), Total Lead Content

Test Method: ASTM F963-17 Clause 8.3.1

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2	3	4	5	7	
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Limit (mg/kg)
Total Lead (Pb)	ND	ND	ND	ND	ND	90
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	8					
Test Item	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Limit (mg/kg)
Total Lead (Pb)	ND					90
Conclusion	PASS					

### Note:

mg/kg (Milligrams per kilogram) = ppm (Parts per million) = 0.0001 % m/m (Percent by mass)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 18H-009462 Page 12 of 13

### **SPECIMEN DESCRIPTION:**

Specimen No.	Specimen Description	Location		
1	Blue coating	On outer wall (blue style)		
2	Green coating	On outer wall (green style)		
3	Black/ silvery inseparable coating	On outer wall (grey style)		
4	Black plastic (PP-homo)	Lid (all styles)		
5	Translucent soft plastic (Silicone)	Gasket (all styles)		
6	Black foam with adhesive	Bottom patch (all styles)		
7	Silvery metal	Inner wall (all styles)		
8	Dull silvery metal	Outer wall/ ring/ lid (all styles)		

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



Test Report #: 18H-009462 Page 13 of 13

## **SAMPLE PHOTO:**





-End Report-

QIMA Testing (HK) Limited \* 3/F Liven House, No. 61 – 63 King Yip Street, Kwun Tong, Kowloon, Hong Kong \* Tel: (852)3185 8000.

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of QIMA Testing (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.