



TEST REPORT

Test Report # 17H-005138 Date of Report Issue: July 4, 2017
 Date of Sample Received: June 26, 2017 Pages: Page 1 of 12

CLIENT INFORMATION:

Company: Hit Promotional Products
 Recipient: Nathan Cotter
 Recipient Email: ncotter@hitpromo.net



SAMPLE INFORMATION:

Description:	16oz Light Up Bottle	Purchase Order Number:	206433
Assortment:	4 colors	Agent:	Growth-Sonic
SKU No.:	5654	Country of Origin:	China
Factory No.:	127992	Labeled Age Grade:	-
Country of Distribution:	United States	Recommended Age Grade:	-
Quantity Submitted:	4 pcs (Blue), 3 pcs (Red, Green), 2 pcs (Black)	Tested Age Grade:	-
Testing Period:	06/26/2017 – 07/04/2017		

OVERALL RESULT:



Refer to page 2 for test result summary and appropriate notes.

ANSECO GROUP (HK) LIMITED

Loska Yeung Lok Ka
 Assistant Manager, Chemical Laboratory

ANSECO GROUP (HK) LIMITED ♦ 3/F Liven House ♦ No. 61 – 63 King Yip Street♦ Kwun Tong♦ Kowloon ♦Hong Kong ♦Tel: (852)31858000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



TEST RESULTS SUMMARY:

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	CPSIA Section 101, Total Lead in Substrate Materials
PASS	Client’s Requirement, Bisphenol A and Bisphenol S [#]
PASS	FDA 21 CFR 177.1210, Closures with Sealing Gaskets [#]
PASS	FDA 21 CFR 177.1630, Polyethylene Phthalate Polymers
PASS	FDA 21 CFR 180.22 and 181.32, Acrylonitrile/Butadiene/Styrene Copolymers
PASS	US Public Law 104-142 Title II, Mercury-Containing Battery Management Act [#]
PASS	Canadian Consumer Products Containing Lead (Contact with Mouth) Regulation SOR/2010-273 as Amended by SOR/2016-171, Total Lead in Accessible Substrates

The above test(s) is/are accredited under the laboratory’s ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with ‘#’ is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

**DETAILED RESULTS:****CPSIA Section 101, Total Lead in Substrate Materials**

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2+3	4+5+6	7+8+9	10+11	12	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	13	---	---	---	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	38	---	---	---	---	100
Conclusion	PASS	---	---	---	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:****Client's Requirement, Bisphenol A and Bisphenol S**

Test Method: AI|ANSECO Method#
 Analytical Method: Liquid Chromatography with Mass Spectrometry

Specimen No.		5	6	7	8	Limit (ppb)
Test Item	CAS No.	Result (ppb)	Result (ppb)	Result (ppb)	Result (ppb)	
Bisphenol A (BPA)	80-05-7	ND	ND	ND	ND	ND
Bisphenol S (BPS)	80-09-1	ND	ND	ND	ND	ND
Conclusion		PASS	PASS	PASS	PASS	

Specimen No.		9	10	---	---	Limit (ppb)
Test Item	CAS No.	Result (ppb)	Result (ppb)	Result (ppb)	Result (ppb)	
Bisphenol A (BPA)	80-05-7	ND	ND	---	---	ND
Bisphenol S (BPS)	80-09-1	ND	ND	---	---	ND
Conclusion		PASS	PASS	---	---	

Note:

ppb (Parts per billion) = $\mu\text{g}/\text{kg}$ (Micrograms per kilogram)

NA = Not applicable

LT = Less than

ND = Not detected (Reporting limit: BPA = 1000 ppb; BPS = 200 ppb)



DETAILED RESULTS:

FDA 21 CFR 177.1210, Closures with Sealing Gaskets

Test Method: FDA 21 CFR 177.1210#

Specimen No.			10	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (ppm)	Fill boiling, cool to 100°F	65 minutes	ND	10	50
Conclusion			PASS		

Note:

Temp. = Temperature

°F = Degree Fahrenheit

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1210 Table 2 Section 2.

The above test(s) is/are accredited under the laboratory’s ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with ‘#’ is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



DETAILED RESULTS:

FDA 21 CFR 177.1630, Polyethylene Phthalate Polymers

Test Method: FDA 21 CFR 177.1630

Specimen No.			9	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in ²)	250°F	2 hours	ND	0.1	0.5
n-Heptane extractive (mg/in ²)	150°F	2 hours	ND	0.1	0.5
Conclusion			PASS		

Note:

Temp. = Temperature

°F = Degree Fahrenheit

mg/in² = Milligrams per square inch

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1630 (f).

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

**DETAILED RESULTS:****FDA 21 CFR 180.22 and 181.32, Acrylonitrile/Butadiene/Styrene Copolymers**

Test Method: FDA 21 CFR 180.22 and 181.32

Analytical Method: Headspace-Gas Chromatography with Mass Spectrometry

Acrylonitrile Monomers:

Specimen No.			5	RL	Limit
Test Simulant	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in ²)	120°F	2 hours	ND	0.001	0.003
3% Acetic acid extractive (mg/in ²)	120°F	2 hours	ND	0.001	0.003
Conclusion			PASS		

Specimen No.			6	RL	Limit
Test Simulant	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in ²)	120°F	2 hours	ND	0.001	0.003
3% Acetic acid extractive (mg/in ²)	120°F	2 hours	ND	0.001	0.003
Conclusion			PASS		

Note:

Temp. = Temperature

°F = Degree Fahrenheit

mg/in² = Milligrams per square inch

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 181.32 (b) (3).

**DETAILED RESULTS:****FDA 21 CFR 180.22 and 181.32, Acrylonitrile/Butadiene/Styrene Copolymers**

Test Method: FDA 21 CFR 180.22 and 181.32

Analytical Method: Headspace-Gas Chromatography with Mass Spectrometry

Acrylonitrile Monomers:

Specimen No.			7	RL	Limit
Test Simulant	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in ²)	120°F	2 hours	ND	0.001	0.003
3% Acetic acid extractive (mg/in ²)	120°F	2 hours	ND	0.001	0.003
Conclusion			PASS		

Specimen No.			8	RL	Limit
Test Simulant	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in ²)	120°F	2 hours	ND	0.001	0.003
3% Acetic acid extractive (mg/in ²)	120°F	2 hours	ND	0.001	0.003
Conclusion			PASS		

Note:

Temp. = Temperature

°F = Degree Fahrenheit

mg/in² = Milligrams per square inch

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 181.32 (b) (3).



DETAILED RESULTS:

US Public Law 104-142 Title II, Mercury-Containing Battery Management Act

Test Method: AI|ANSECO Method#
Analytical Method: Atomic Absorption Spectrometry with Cold-Vapor Technique

Button cells

Specimen No.	14	---	---	---	---	Total Limit (mg/cell)
Test Item	Result (mg/cell)	Result (mg/cell)	Result (mg/cell)	Result (mg/cell)	Result (mg/cell)	
Total Mercury (Hg)	ND	---	---	---	---	25
Conclusion	PASS	---	---	---	---	

Note:
mg/cell = Milligrams per cell
LT = Less than
ND = Not detected (Reporting Limit = 1 mg/cell)

The above test(s) is/are accredited under the laboratory’s ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with ‘#’ is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

**DETAILED RESULTS:****Canadian Consumer Products Containing Lead (Contact with Mouth) Regulation SOR/2010-273 as Amended by SOR/2016-171, Total Lead in Accessible Substrates**

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2+3	4+5+6	7+8+9	10+11	12	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	90
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	13	---	---	---	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	38	---	---	---	---	90
Conclusion	PASS	---	---	---	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**SPECIMEN DESCRIPTION:**

Specimen No.	Specimen Description	Location
1	Red plastic (ABS)	Lid (red style)
2	Blue plastic (ABS)	Lid (blue style)
3	Green plastic (ABS)	Lid (green style)
4	Black plastic (ABS)	Lid (black style)
5	Transparent red plastic (Food grade ABS)	Lower lid (red style)
6	Transparent blue plastic (Food grade ABS)	Lower lid (blue style)
7	Transparent green plastic (Food grade ABS)	Lower lid (green style)
8	Transparent grey plastic (Food grade ABS)	Lower lid (black style)
9	Transparent plastic (Tritan)	Bottle (all styles)
10	Translucent soft plastic	Ring (all styles)
11	Black soft plastic	Button (all styles)
12	Silvery metal	Spring in battery compartment (all styles)
13	Golden metal	Plate in battery compartment (all styles)
14	Silvery button cell	Button cell (all styles)



Test Report #

17H-005138

Pages:

Page 12 of 12

SAMPLE PHOTO:



-End Report-

ANSECO GROUP (HK) LIMITED ♦ 3/F Liven House ♦ No. 61 – 63 King Yip Street♦ Kwun Tong♦ Kowloon ♦Hong Kong ♦Tel: (852)31858000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.