




TEST REPORT

Test Report # 17H-004979 Date of Report Issue: July 10, 2017
 Date of Sample Received: June 21, 2017 Pages: Page 1 of 12

CLIENT INFORMATION:

Company: Hit Promotional Products
 Recipient: Nathan Cotter
 Recipient Email: ncotter@hitpromo.net



SAMPLE INFORMATION:

Description:	16oz Double Wall Aria Tumbler		
Assortment:	3 colors	Purchase Order Number:	211362
SKU No.:	5810	Agent:	Brand New Days
Factory No.:	106712	Country of Origin:	China
Country of Distribution:	United States	Labeled Age Grade:	-
Quantity Submitted:	5 pcs per style	Recommended Age Grade:	-
Testing Period:	06/21/2017 – 06/29/2017 07/03/2017 – 07/10/2017	Tested Age Grade:	-

OVERALL RESULT:



Refer to page 2 for test result summary and appropriate notes.

ANSECO GROUP (HK) LIMITED

Loska Yeung LokKa
 Assistant Manager, Chemical Laboratory

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street • Kwun Tong • Kowloon • Hong Kong • Tel: (852)31858000

*The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.
 This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.*

**TEST RESULTS SUMMARY:**

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	CPSIA Section 101, Total Lead in Substrate Materials
PASS	Client's Requirement, Bisphenol A and Bisphenol S [#]
PASS	FDA 21 CFR 177.1210, Closures with Sealing Gaskets [#]
PASS	FDA 21 CFR 177.1520, Polypropylene Homopolymers
PASS	FDA 21 CFR 180.22 and 181.32, Acrylonitrile/Styrene Copolymers
PASS	Canadian Consumer Products Containing Lead (Contact with Mouth) Regulation SOR/2010-273 as Amended by SOR/2016-171, Total Lead in Accessible Substrates



DETAILED RESULTS:

CPSIA Section 101, Total Lead in Substrate Materials

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2	3+4	6	7+8	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	---	100
Conclusion	PASS	PASS	PASS	PASS	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:****Client's Requirement, Bisphenol A and Bisphenol S**Test Method: AI|ANSECO Method[#]

Analytical Method: Liquid Chromatography with Mass Spectrometry

Specimen No.		2	3	4	5	Limit (ppb)
Test Item	CAS No.	Result (ppb)	Result (ppb)	Result (ppb)	Result (ppb)	
Bisphenol A (BPA)	80-05-7	ND	ND	ND	ND	ND
Bisphenol S (BPS)	80-09-1	ND	ND	ND	ND	ND
Conclusion		PASS	PASS	PASS	PASS	

Specimen No.		6	7	8	---	Limit (ppb)
Test Item	CAS No.	Result (ppb)	Result (ppb)	Result (ppb)	Result (ppb)	
Bisphenol A (BPA)	80-05-7	ND	ND	ND	---	ND
Bisphenol S (BPS)	80-09-1	ND	ND	ND	---	ND
Conclusion		PASS	PASS	PASS	---	

Note:

ppb (Parts per billion) = µg/kg (Micrograms per kilogram)

NA = Not applicable

LT = Less than

ND = Not detected (Reporting limit: BPA = 1000 ppb; BPS = 200 ppb)



DETAILED RESULTS:

FDA 21 CFR 177.1210, Closures with Sealing Gaskets

Test Method: FDA 21 CFR 177.1210[#]

Specimen No.			6	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (ppm)	120°F	24 hours	ND	10	50
Conclusion			PASS		

Note:

Temp. = Temperature

°F = Degree Fahrenheit

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1210 Table 2 Section 2.

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

**DETAILED RESULTS:****FDA 21 CFR 177.1520, Polypropylene Homopolymers**

Test Method: FDA 21 CFR 177.1520

Specimen No.			3	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.894	NA	0.880 – 0.913
Melting point (°C)	NA	NA	163.5	NA	150 – 180
n-Hexane extractive (% w/w)	Reflux	2 hours	0.8	0.1	6.4
Xylene extractive (% w/w)	25°C	1 hour	2.2	0.5	9.8
Conclusion			PASS		

Specimen No.			4	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.898	NA	0.880 – 0.913
Melting point (°C)	NA	NA	163.2	NA	150 – 180
n-Hexane extractive (% w/w)	Reflux	2 hours	0.8	0.1	6.4
Xylene extractive (% w/w)	25°C	1 hour	2.6	0.5	9.8
Conclusion			PASS		

Note:

Temp. = Temperature

°C = Degree Celsius

g/cc = Grams per cubic centimeter

%w/w = Percent by weight

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1520 (c) 1.1.

**DETAILED RESULTS:****FDA 21 CFR 177.1520, Polypropylene Homopolymers**

Test Method: FDA 21 CFR 177.1520

Specimen No.			8	RL	Limit
Test Item	Test Condition		Result		
	Temp.	Duration			
Density (g/cc)	NA	NA	0.900	NA	0.880 – 0.913
Melting point (°C)	NA	NA	164.1	NA	150 – 180
n-Hexane extractive (% w/w)	Reflux	2 hours	0.5	0.1	6.4
Xylene extractive (% w/w)	25°C	1 hour	2.3	0.5	9.8
Conclusion			PASS		

Note:

Temp. = Temperature

°C = Degree Celsius

g/cc = Grams per cubic centimeter

%w/w = Percent by weight

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1520 (c) 1.1.

**DETAILED RESULTS:****FDA 21 CFR 180.22 and 181.32, Acrylonitrile/Styrene Copolymers**

Test Method: FDA 21 CFR 180.22 and 181.32

Analytical Method: Headspace-Gas Chromatography with Mass Spectrometry

Acrylonitrile Monomers:

Specimen No.			2	RL	Limit
Test Simulant	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in ²)	120°F	2 hours	ND	0.001	0.003
3% Acetic acid extractive (mg/in ²)	120°F	2 hours	ND	0.001	0.003
Conclusion			PASS		

Specimen No.			5	RL	Limit
Test Simulant	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in ²)	120°F	2 hours	ND	0.001	0.003
3% Acetic acid extractive (mg/in ²)	120°F	2 hours	ND	0.001	0.003
Conclusion			PASS		

Note:

Temp. = Temperature

°F = Degree Fahrenheit

mg/in² = Milligrams per square inch

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 181.32 (b) (3).



DETAILED RESULTS:

FDA 21 CFR 180.22 and 181.32, Acrylonitrile/Styrene Copolymers

Test Method: FDA 21 CFR 180.22 and 181.32

Analytical Method: Headspace-Gas Chromatography with Mass Spectrometry

Acrylonitrile Monomers:

Specimen No.			7	RL	Limit
Test Simulant	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in ²)	120°F	2 hours	ND	0.001	0.003
3% Acetic acid extractive (mg/in ²)	120°F	2 hours	ND	0.001	0.003
Conclusion			PASS		

Note:

Temp. = Temperature

°F = Degree Fahrenheit

mg/in² = Milligrams per square inch

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 181.32 (b) (3).

**DETAILED RESULTS:****Canadian Consumer Products Containing Lead (Contact with Mouth) Regulation SOR/2010-273 as Amended by SOR/2016-171, Total Lead in Accessible Substrates**

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1+2	3+4	6	7+8	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	---	90
Conclusion	PASS	PASS	PASS	PASS	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**SPECIMEN DESCRIPTION:**

Specimen No.	Specimen Description	Location
1	Clear plastic	Outer wall (all styles); Inner wall/ lid (clear styles)
2	Clear black plastic (AS)	Lid/ inner wall (black style)
3	Translucent plastic (PP-homo)	Straw (clear style); ring of straw (all styles)
4	Translucent black plastic (PP-homo)	Straw (black style)
5	Clear plastic (AS)	Lid/ inner wall (clear style)
6	Translucent soft plastic (Silicone)	Gasket (all styles)
7	Clear blue plastic (AS)	Lid/ inner wall (blue style)
8	Translucent blue plastic (PP-homo)	Straw (blue style)



SAMPLE PHOTO:



-End Report-

ANSECO GROUP (HK) LIMITED ♦ 3/F Liven House ♦ No. 61 – 63 King Yip Street♦Kwun Tong♦ Kowloon ♦Hong Kong ♦Tel: (852)31858000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.