

TEST REPORT

| | | | |
|------------------|--------------------------------------|----------------|-------------------|
| Company: | Prime Products Inc. | Test Report # | 15H-05581 |
| Recipient: | Elyse Kristinik/ Heather Barnett | Date of Issue: | November 17, 2015 |
| Recipient Email: | elyse.kristinik@primeproductsinc.net | Pages: | Page 1 of 15 |
| cc to Email: | heather.barnett@primeproductsinc.net | Date Received: | November 04, 2015 |

SAMPLE INFORMATION:

| | | | |
|--------------------------|--|------------------------|---------------|
| Description: | PET Bottles: 2063, 2463, 2663, EBO63, 3063, Freedom Bottle, 3263-RSB, Mason Jar | | |
| Assortment: | Translucent Red, Translucent Blue, Translucent Green, Translucent Purple, Translucent Smoke, Translucent Clear, Translucent Orange, Translucent Pink, Translucent Aqua, Lime, Translucent Navy, Translucent Sea Glass, HG White, & HG Black | Purchase Order Number: | - |
| SKU/style No.: | - | Toy Co./Agency: | - |
| Factory/Supplier/Vendor: | - | Country of Origin: | United States |
| Country of Distribution: | - | Labeled Age Grade: | - |
| Quantity Submitted: | 7 pcs per style | Recommended Age Grade: | - |
| Testing Period: | 11/10/2015 – 11/17/2015 | Tested Age Grade: | - |

OVERALL RESULT:

PASS

Refer to page 2 for test result summary and appropriate notes.

ANSECO GROUP (HK) LIMITED



Vincent Chow Wai Kit
Manager, Chemical Laboratory

ANSECO GROUP (HK) LIMITED



Stepford Ho King Ho
Leader, Physical Laboratory

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

TEST REPORT

| | | | |
|------------------|--------------------------------------|----------------|-------------------|
| Company: | Prime Products Inc. | Test Report # | 15H-05581 |
| Recipient: | Elyse Kristinik/ Heather Barnett | Date of Issue: | November 17, 2015 |
| Recipient Email: | elyse.kristinik@primeproductsinc.net | Pages: | Page 2 of 15 |
| cc to Email: | heather.barnett@primeproductsinc.net | Date Received: | November 04, 2015 |

At the request of the client, the following tests were conducted:

| CONCLUSION | TEST(S) CONDUCTED |
|------------|---|
| PASS | CPSIA Section 101, Total Lead in Substrate Materials |
| PASS | California Proposition 65, Total Lead in Substrate Materials |
| PASS | CPSIA Section 108, Phthalates – Mouthable (DBP, BBP, DEHP, DnOP, DINP, DIDP) |
| PASS | California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP) |
| PASS | Client's Requirement: Bisphenol A [#] |
| PASS | FDA 21 CFR 177.1630, Polyethylene Phthalate Polymers |
| PASS | 16 CFR 1500.3(c)(6)(vi), Flammability of Solids Flammable hazards evaluated as described in 16 CFR 1500.44. |

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

TEST REPORT

| | | | |
|------------------|--------------------------------------|----------------|-------------------|
| Company: | Prime Products Inc. | Test Report # | 15H-05581 |
| Recipient: | Elyse Kristinik/ Heather Barnett | Date of Issue: | November 17, 2015 |
| Recipient Email: | elyse.kristinik@primeproductsinc.net | Pages: | Page 3 of 15 |
| cc to Email: | heather.barnett@primeproductsinc.net | Date Received: | November 04, 2015 |

DETAILED RESULTS:

CPSIA Section 101, Total Lead in Substrate Materials

Analysis performed by Inductively Coupled Plasma-Optical Emission Spectrometry to determine compliance with the above referenced regulation.

[Referenced Test Method: CPSC-CH-E1001-08.2 (Metal) and/or CPSC-CH-E1002-08.2 (Non-Metal)]

| Specimen No. | 1+2+3 | 4+5+6 | 7+8+9 | 10+11 | 12+13 | Limit Total (ppm) |
|-------------------|-----------------|-----------------|-----------------|-----------------|-----------------|-------------------------|
| Test Item | Result (ppm) | Result (ppm) | Result (ppm) | Result (ppm) | Result (ppm) | |
| Total Pb | 29 | ND | ND | ND | ND | 100 |
| Conclusion | PASS | PASS | PASS | PASS | PASS | |

Note:

Pb = Lead

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

TEST REPORT

| | | | |
|------------------|--------------------------------------|----------------|-------------------|
| Company: | Prime Products Inc. | Test Report # | 15H-05581 |
| Recipient: | Elyse Kristinik/ Heather Barnett | Date of Issue: | November 17, 2015 |
| Recipient Email: | elyse.kristinik@primeproductsinc.net | Pages: | Page 4 of 15 |
| cc to Email: | heather.barnett@primeproductsinc.net | Date Received: | November 04, 2015 |

DETAILED RESULTS:

California Proposition 65, Total Lead in Substrate Materials

Analysis performed by Inductively Coupled Plasma-Optical Emission Spectrometry to determine compliance with the above referenced specification.

[Referenced Test Method: CPSC-CH-E1001-08.2 (Metal) and/or CPSC-CH-E1002-08.2 (Non-Metal)]

| Specimen No. | 1+2+3 | 4+5+6 | 7+8+9 | 10+11 | 12+13 | Limit |
|-------------------|--------------|--------------|--------------|--------------|--------------|-------------|
| Test Item | Result (ppm) | Result (ppm) | Result (ppm) | Result (ppm) | Result (ppm) | Total (ppm) |
| Total Pb | 29 | ND | ND | ND | ND | 100 |
| Conclusion | PASS | PASS | PASS | PASS | PASS | |

Note:

Pb = Lead

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

TEST REPORT

| | | | |
|------------------|--------------------------------------|----------------|-------------------|
| Company: | Prime Products Inc. | Test Report # | 15H-05581 |
| Recipient: | Elyse Kristinik/ Heather Barnett | Date of Issue: | November 17, 2015 |
| Recipient Email: | elyse.kristinik@primeproductsinc.net | Pages: | Page 5 of 15 |
| cc to Email: | heather.barnett@primeproductsinc.net | Date Received: | November 04, 2015 |

DETAILED RESULTS:

CPSIA Section 108, Phthalates – Mouthable (DBP, BBP, DEHP, DnOP, DINP, DIDP)

Analysis performed by Gas Chromatography/Mass Spectrometry to determine compliance with the above referenced regulation. [Referenced Test Method: CPSC-CH-C1001-09.3]

| Specimen No. | 1+2+3 | 4+5+6 | 7+8+9 | 10+11 | 12+13 | Limit (ppm) |
|-------------------|--------------|--------------|--------------|--------------|--------------|-------------|
| Test Item | Result (ppm) | Result (ppm) | Result (ppm) | Result (ppm) | Result (ppm) | |
| DBP | ND | ND | ND | ND | ND | 1000 |
| BBP | ND | ND | ND | ND | ND | 1000 |
| DEHP | ND | ND | ND | ND | ND | 1000 |
| DnOP | ND | ND | ND | ND | ND | 1000 |
| DINP | ND | ND | ND | ND | ND | 1000 |
| DIDP | ND | ND | ND | ND | ND | 1000 |
| Conclusion | PASS | PASS | PASS | PASS | PASS | |

Note:

DBP = Dibutyl phthalate; BBP = Benzyl butyl phthalate; DEHP = Di-(2-ethylhexyl) phthalate

DnOP = Di-n-octyl phthalate; DINP = Diisononyl phthalate; DIDP = Diisodecyl phthalate

ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % w/w (Percent by weight)

LT = Less than

ND = Not detected (Reporting Limit = 120ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

TEST REPORT

| | | | |
|------------------|--------------------------------------|----------------|-------------------|
| Company: | Prime Products Inc. | Test Report # | 15H-05581 |
| Recipient: | Elyse Kristinik/ Heather Barnett | Date of Issue: | November 17, 2015 |
| Recipient Email: | elyse.kristinik@primeproductsinc.net | Pages: | Page 6 of 15 |
| cc to Email: | heather.barnett@primeproductsinc.net | Date Received: | November 04, 2015 |

DETAILED RESULTS:

California Proposition 65, Phthalates (DBP, BBP, DEHP, DINP, DIDP, DnHP)

Analysis performed by Gas Chromatography/Mass Spectrometry to determine compliance with the above referenced specification. [Referenced Test Method: CPSC-CH-C1001-09.3]

| Specimen No. | 1+2+3 | 4+5+6 | 7+8+9 | 10+11 | 12+13 | Limit (ppm) |
|-------------------|--------------|--------------|--------------|--------------|--------------|-------------|
| Test Item | Result (ppm) | Result (ppm) | Result (ppm) | Result (ppm) | Result (ppm) | |
| DBP | ND | ND | ND | ND | ND | 1000 |
| BBP | ND | ND | ND | ND | ND | 1000 |
| DEHP | ND | ND | ND | ND | ND | 1000 |
| DINP | ND | ND | ND | ND | ND | 1000 |
| DIDP | ND | ND | ND | ND | ND | 1000 |
| DnHP | ND | ND | ND | ND | ND | 1000 |
| Conclusion | PASS | PASS | PASS | PASS | PASS | |

Note:

DBP = Dibutyl phthalate; BBP = Benzyl butyl phthalate; DEHP = Di-(2-ethylhexyl) phthalate
 DINP = Diisononyl phthalate, DIDP = Diisodecyl phthalate; DnHP = Di-n-hexyl phthalate
 ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % w/w (Percent by weight)
 LT = Less than

ND = Not detected (Reporting Limit = 120ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.
 This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.
 ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

TEST REPORT

| | | | |
|------------------|--------------------------------------|----------------|-------------------|
| Company: | Prime Products Inc. | Test Report # | 15H-05581 |
| Recipient: | Elyse Kristinik/ Heather Barnett | Date of Issue: | November 17, 2015 |
| Recipient Email: | elyse.kristinik@primeproductsinc.net | Pages: | Page 7 of 15 |
| cc to Email: | heather.barnett@primeproductsinc.net | Date Received: | November 04, 2015 |

DETAILED RESULTS:

Client's Requirement: Bisphenol A

Analysis performed by High Performance Liquid Chromatography with Fluorescence Detector to determine compliance with the above specification. [Referenced Test Method: AI|ANSECO Method#]

| Specimen No. | 1 | 2 | 3 | 4 | 5 | Limit (ppm) |
|-------------------|--------------|--------------|--------------|--------------|--------------|-------------|
| Test Item | Result (ppm) | Result (ppm) | Result (ppm) | Result (ppm) | Result (ppm) | |
| Bisphenol A | ND | ND | ND | ND | ND | ND |
| Conclusion | PASS | PASS | PASS | PASS | PASS | |

| Specimen No. | 6 | 7 | 8 | 9 | 10 | Limit (ppm) |
|-------------------|--------------|--------------|--------------|--------------|--------------|-------------|
| Test Item | Result (ppm) | Result (ppm) | Result (ppm) | Result (ppm) | Result (ppm) | |
| Bisphenol A | ND | ND | ND | ND | ND | ND |
| Conclusion | PASS | PASS | PASS | PASS | PASS | |

| Specimen No. | 11 | 12 | 13 | --- | --- | Limit (ppm) |
|-------------------|--------------|--------------|--------------|--------------|--------------|-------------|
| Test Item | Result (ppm) | Result (ppm) | Result (ppm) | Result (ppm) | Result (ppm) | |
| Bisphenol A | ND | ND | ND | --- | --- | ND |
| Conclusion | PASS | PASS | PASS | --- | --- | |

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not Detected (Reporting limit = 1 ppm)

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein. This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited. ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

TEST REPORT

| | | | |
|------------------|--------------------------------------|----------------|-------------------|
| Company: | Prime Products Inc. | Test Report # | 15H-05581 |
| Recipient: | Elyse Kristinik/ Heather Barnett | Date of Issue: | November 17, 2015 |
| Recipient Email: | elyse.kristinik@primeproductsinc.net | Pages: | Page 8 of 15 |
| cc to Email: | heather.barnett@primeproductsinc.net | Date Received: | November 04, 2015 |

DETAILED RESULTS:

FDA 21 CFR 177.1630, Polyethylene Phthalate Polymers

Analysis performed by food simulating solvents extractions to determine compliance with above referenced regulation. [Referenced Test Method: FDA 21 CFR 177.1630]

| Specimen No. | | | 1 | RL | Specification |
|--|----------------|----------|--------|------------|---------------|
| Test Item | Test Condition | | Result | | |
| | Temperature | Duration | | | |
| Distilled water extractive (mg/in ²) | 250°F | 2 hours | ND | 0.1 | 0.5 |
| n-Heptane extractive (mg/in ²) | 150°F | 2 hours | ND | 0.1 | 0.5 |
| Conclusion | | | PASS | | |

| Specimen No. | | | 2 | RL | Specification |
|--|----------------|----------|--------|------------|---------------|
| Test Item | Test Condition | | Result | | |
| | Temperature | Duration | | | |
| Distilled water extractive (mg/in ²) | 250°F | 2 hours | ND | 0.1 | 0.5 |
| n-Heptane extractive (mg/in ²) | 150°F | 2 hours | ND | 0.1 | 0.5 |
| Conclusion | | | PASS | | |

| Specimen No. | | | 3 | RL | Specification |
|--|----------------|----------|--------|------------|---------------|
| Test Item | Test Condition | | Result | | |
| | Temperature | Duration | | | |
| Distilled water extractive (mg/in ²) | 250°F | 2 hours | ND | 0.1 | 0.5 |
| n-Heptane extractive (mg/in ²) | 150°F | 2 hours | ND | 0.1 | 0.5 |
| Conclusion | | | PASS | | |

Note:

°F = Degree Fahrenheit
 mg/in² = Milligrams per square inch
 LT = Less than
 ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1630 (f).

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

TEST REPORT

| | | | |
|------------------|--------------------------------------|----------------|-------------------|
| Company: | Prime Products Inc. | Test Report # | 15H-05581 |
| Recipient: | Elyse Kristinik/ Heather Barnett | Date of Issue: | November 17, 2015 |
| Recipient Email: | elyse.kristinik@primeproductsinc.net | Pages: | Page 9 of 15 |
| cc to Email: | heather.barnett@primeproductsinc.net | Date Received: | November 04, 2015 |

DETAILED RESULTS:

FDA 21 CFR 177.1630, Polyethylene Phthalate Polymers

Analysis performed by food simulating solvents extractions to determine compliance with above referenced regulation. [Referenced Test Method: FDA 21 CFR 177.1630]

| Specimen No. | | | 4 | RL | Specification |
|--|----------------|----------|--------|-----|---------------|
| Test Item | Test Condition | | Result | | |
| | Temperature | Duration | | | |
| Distilled water extractive (mg/in ²) | 250°F | 2 hours | ND | 0.1 | 0.5 |
| n-Heptane extractive (mg/in ²) | 150°F | 2 hours | ND | 0.1 | 0.5 |
| Conclusion | | | PASS | | |

| Specimen No. | | | 5 | RL | Specification |
|--|----------------|----------|--------|-----|---------------|
| Test Item | Test Condition | | Result | | |
| | Temperature | Duration | | | |
| Distilled water extractive (mg/in ²) | 250°F | 2 hours | ND | 0.1 | 0.5 |
| n-Heptane extractive (mg/in ²) | 150°F | 2 hours | ND | 0.1 | 0.5 |
| Conclusion | | | PASS | | |

| Specimen No. | | | 6 | RL | Specification |
|--|----------------|----------|--------|-----|---------------|
| Test Item | Test Condition | | Result | | |
| | Temperature | Duration | | | |
| Distilled water extractive (mg/in ²) | 250°F | 2 hours | ND | 0.1 | 0.5 |
| n-Heptane extractive (mg/in ²) | 150°F | 2 hours | ND | 0.1 | 0.5 |
| Conclusion | | | PASS | | |

Note:

°F = Degree Fahrenheit
 mg/in² = Milligrams per square inch
 LT = Less than
 ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1630 (f).

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

TEST REPORT

| | | | |
|------------------|--------------------------------------|----------------|-------------------|
| Company: | Prime Products Inc. | Test Report # | 15H-05581 |
| Recipient: | Elyse Kristinik/ Heather Barnett | Date of Issue: | November 17, 2015 |
| Recipient Email: | elyse.kristinik@primeproductsinc.net | Pages: | Page 10 of 15 |
| cc to Email: | heather.barnett@primeproductsinc.net | Date Received: | November 04, 2015 |

DETAILED RESULTS:

FDA 21 CFR 177.1630, Polyethylene Phthalate Polymers

Analysis performed by food simulating solvents extractions to determine compliance with above referenced regulation. [Referenced Test Method: FDA 21 CFR 177.1630]

| Specimen No. | | | 7 | RL | Specification |
|--|----------------|----------|--------|------------|---------------|
| Test Item | Test Condition | | Result | | |
| | Temperature | Duration | | | |
| Distilled water extractive (mg/in ²) | 250°F | 2 hours | ND | 0.1 | 0.5 |
| n-Heptane extractive (mg/in ²) | 150°F | 2 hours | ND | 0.1 | 0.5 |
| Conclusion | | | PASS | | |

| Specimen No. | | | 8 | RL | Specification |
|--|----------------|----------|--------|------------|---------------|
| Test Item | Test Condition | | Result | | |
| | Temperature | Duration | | | |
| Distilled water extractive (mg/in ²) | 250°F | 2 hours | ND | 0.1 | 0.5 |
| n-Heptane extractive (mg/in ²) | 150°F | 2 hours | ND | 0.1 | 0.5 |
| Conclusion | | | PASS | | |

| Specimen No. | | | 9 | RL | Specification |
|--|----------------|----------|--------|------------|---------------|
| Test Item | Test Condition | | Result | | |
| | Temperature | Duration | | | |
| Distilled water extractive (mg/in ²) | 250°F | 2 hours | ND | 0.1 | 0.5 |
| n-Heptane extractive (mg/in ²) | 150°F | 2 hours | ND | 0.1 | 0.5 |
| Conclusion | | | PASS | | |

Note:

°F = Degree Fahrenheit
 mg/in² = Milligrams per square inch
 LT = Less than
 ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1630 (f).

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

TEST REPORT

| | | | |
|------------------|--------------------------------------|----------------|-------------------|
| Company: | Prime Products Inc. | Test Report # | 15H-05581 |
| Recipient: | Elyse Kristinik/ Heather Barnett | Date of Issue: | November 17, 2015 |
| Recipient Email: | elyse.kristinik@primeproductsinc.net | Pages: | Page 11 of 15 |
| cc to Email: | heather.barnett@primeproductsinc.net | Date Received: | November 04, 2015 |

DETAILED RESULTS:

FDA 21 CFR 177.1630, Polyethylene Phthalate Polymers

Analysis performed by food simulating solvents extractions to determine compliance with above referenced regulation. [Referenced Test Method: FDA 21 CFR 177.1630]

| Specimen No. | | | 10 | RL | Specification |
|--|----------------|----------|--------|------------|---------------|
| Test Item | Test Condition | | Result | | |
| | Temperature | Duration | | | |
| Distilled water extractive (mg/in ²) | 250°F | 2 hours | ND | 0.1 | 0.5 |
| n-Heptane extractive (mg/in ²) | 150°F | 2 hours | ND | 0.1 | 0.5 |
| Conclusion | | | PASS | | |

| Specimen No. | | | 11 | RL | Specification |
|--|----------------|----------|--------|------------|---------------|
| Test Item | Test Condition | | Result | | |
| | Temperature | Duration | | | |
| Distilled water extractive (mg/in ²) | 250°F | 2 hours | ND | 0.1 | 0.5 |
| n-Heptane extractive (mg/in ²) | 150°F | 2 hours | ND | 0.1 | 0.5 |
| Conclusion | | | PASS | | |

| Specimen No. | | | 12 | RL | Specification |
|--|----------------|----------|--------|------------|---------------|
| Test Item | Test Condition | | Result | | |
| | Temperature | Duration | | | |
| Distilled water extractive (mg/in ²) | 250°F | 2 hours | ND | 0.1 | 0.5 |
| n-Heptane extractive (mg/in ²) | 150°F | 2 hours | ND | 0.1 | 0.5 |
| Conclusion | | | PASS | | |

Note:

°F = Degree Fahrenheit
 mg/in² = Milligrams per square inch
 LT = Less than
 ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1630 (f).

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

TEST REPORT

| | | | |
|------------------|--------------------------------------|----------------|-------------------|
| Company: | Prime Products Inc. | Test Report # | 15H-05581 |
| Recipient: | Elyse Kristinik/ Heather Barnett | Date of Issue: | November 17, 2015 |
| Recipient Email: | elyse.kristinik@primeproductsinc.net | Pages: | Page 12 of 15 |
| cc to Email: | heather.barnett@primeproductsinc.net | Date Received: | November 04, 2015 |

DETAILED RESULTS:

FDA 21 CFR 177.1630, Polyethylene Phthalate Polymers

Analysis performed by food simulating solvents extractions to determine compliance with above referenced regulation. [Referenced Test Method: FDA 21 CFR 177.1630]

| Specimen No. | | | 13 | RL | Specification |
|--|----------------|----------|--------|------------|---------------|
| Test Item | Test Condition | | Result | | |
| | Temperature | Duration | | | |
| Distilled water extractive (mg/in ²) | 250°F | 2 hours | ND | 0.1 | 0.5 |
| n-Heptane extractive (mg/in ²) | 150°F | 2 hours | ND | 0.1 | 0.5 |
| Conclusion | | | PASS | | |

Note:

°F = Degree Fahrenheit
 mg/in² = Milligrams per square inch
 LT = Less than
 ND = Not detected. Result value is less than reporting limit (RL).

Remark:


The specification is quoted from 21 CFR 177.1630 (f).

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



TEST REPORT

Company: Prime Products Inc.
 Recipient: Elyse Kristinik/ Heather Barnett
 Recipient Email: elyse.kristinik@primeproductsinc.net
 cc to Email: heather.barnett@primeproductsinc.net

Test Report # 15H-05581
 Date of Issue: November 17, 2015
 Pages: Page 13 of 15
 Date Received: November 04, 2015

DETAILED RESULTS:

16 CFR 1500.3(c)(6)(vi), Flammability of Solids

Flammable hazards evaluated as described in 16 CFR 1500.44.

| Test | Conclusion | Observation |
|------------------------|------------|--|
| Flammability of Solids | PASS | No Ignition The content is not defined as flammable solid according to 16 CFR 1500.3(c)(6)(vi). |

*The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.
 The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.
 This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.*

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

TEST REPORT

Company: Prime Products Inc.
 Recipient: Elyse Kristinik/ Heather Barnett
 Recipient Email: elyse.kristinik@primeproductsinc.net
 cc to Email: heather.barnett@primeproductsinc.net

Test Report # 15H-05581
 Date of Issue: November 17, 2015
 Pages: Page 14 of 15
 Date Received: November 04, 2015

SPECIMEN DESCRIPTION:

| Specimen No. | Specimen Description | Location |
|--------------|---------------------------------------|---|
| 1 | Translucent red plastic (PET) | Bottle (2463 - red/ 3263-RSB - red/ Mason Jar - red styles) |
| 2 | Translucent orange plastic (PET) | Bottle (EBO63 - orange style) |
| 3 | Translucent green plastic (PET) | Bottle (Freed Bottle - Sea glass/ Mason Jar - sea glass styles) |
| 4 | Translucent light green plastic (PET) | Bottle (EBO63 - sea glass style) |
| 5 | Translucent deep green plastic (PET) | Bottle (2663 - green/ Mason Jar - lime styles) |
| 6 | Translucent blue plastic (PET) | Bottle (2463 - navy blue/ Freed Bottle - blue styles) |
| 7 | Translucent light blue plastic (PET) | Bottle (2063 - blue/ 2463 - blue/ Freed Bottle - light blue/ Mason Jar - blue styles) |
| 8 | Translucent purple plastic (PET) | Bottle (2063 - purple/ Mason Jar - purple styles) |
| 9 | Translucent pink plastic (PET) | Bottle (EBO63 - pink/ Freed Bottle - pink styles) |
| 10 | Translucent grey plastic (PET) | Bottle (3063 - smoke/ 3263-RSB - smoke/ Mason Jar - smoke styles) |
| 11 | Clear plastic (PET) | Bottle (2063 - clear/ 3263-RSB - clear/ Mason Jar - clear styles) |
| 12 | White plastic (PET) | Bottle (Freed Bottle - HG white style) |
| 13 | Black plastic (PET) | Bottle (Freed Bottle - HG black style) |

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

TEST REPORT

Company: Prime Products Inc.
Recipient: Elyse Kristinik/ Heather Barnett
Recipient Email: elyse.kristinik@primeproductsinc.net
cc to Email: heather.barnett@primeproductsinc.net

Test Report # 15H-05581
Date of Issue: November 17, 2015
Pages: Page 15 of 15
Date Received: November 04, 2015

SAMPLE PHOTO:



-End Report-

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.