





Company: Huffermen, Inc.

Recipient: Eric Miller

Recipient Email: eric@huffermen.com

cc to Email:

Test Report #

15H-01386

Date of Issue:

April 10, 2015

Pages:

Page 1 of 8

Date Received:

March 26, 2015

#### **SAMPLE INFORMATION:**

Description:

LDPE Bottles

Assortment: Product ID:

PRO24, PRO32

Purchase Order Number:

Toy Co./Agency:

Country of Origin:

Labeled Age Grade:

Country of Distribution: **Quantity Submitted:** 

Factory/Supplier/Vendor:

3 pcs per style

Requested Age Grade:

3+

Testing Period:

03/31/2015 - 04/10/2015

Tested Age Grade:

Over 3 years of age

**OVERALL RESULT:** 

**PASS** 

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	CPSIA Section 101, Total Lead in Substrate Materials
PASS	CPSIA Section 108, Phthalates – Mouthable (DBP, BBP, DEHP, DnOP, DINP, DIDP)
PASS	FDA 21 CFR 177.1520, Polyethylene
PASS	16 CFR 1500, Federal Hazardous Substances Act (FHSA), Mechanical Hazards
PASS	16 CFR 1500.3(c)(6)(vi), Flammability of Solids

ANSECO GROUP (HK) LIMITED

ANSECO GROUP (HK) LIMITED

Vincent Chow Wai Kit

Manager, Chemical Laboratory

Joseph Kwan Tsz Hung Assistant Manager, Physical Laboratory





Test Report #

Date of Issue:

Pages:



15H-01386

Page 2 of 8

April 10, 2015

# TEST REPORT

Company: Huffermen, Inc.

Recipient: Eric Miller

Recipient Email: eric@huffermen.com

cc to Email: - Date Received: March 26, 2015

#### **DETAILED RESULTS:**

# **CPSIA Section 101, Total Lead in Substrate Materials**

Analysis performed by Inductively Coupled Plasma-Optical Emission Spectrometry to determine compliance with the above referenced regulation.

[Referenced Test Method: CPSC-CH-E1001-08.2 (Metal) and/or CPSC-CH-E1002-08.2 (Non-Metal)]

Specimen No.	1+2+3					Limit
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Total (ppm)
Total Pb	ND					100
Conclusion	PASS					

Note:

Pb = Lead

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.







Company: Huffermen, Inc.

Recipient: Eric Miller

Recipient Email: eric@huffermen.com

cc to Email: - Date Receive

Test Report # 15H-01386

Date of Issue: April 10, 2015

Pages: Page 3 of 8

Date Received: March 26, 2015

### **DETAILED RESULTS:**

# CPSIA Section 108, Phthalates - Mouthable (DBP, BBP, DEHP, DnOP, DINP, DIDP)

Analysis performed by Gas Chromatography/Mass Spectrometry to determine compliance with the above referenced regulation. [Referenced Test Method: CPSC-CH-C1001-09.3]

Specimen No.	1+2+3					
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Limit (ppm)
DBP	ND					1000
BBP	ND					1000
DEHP	ND					1000
DnOP	ND					1000
DINP	ND					1000
DIDP	ND					1000
Conclusion	PASS					

#### Note:

DBP = Dibutyl phthalate; BBP = Benzyl butyl phthalate; DEHP = Di-(2-ethylhexyl) phthalate DnOP = Di-n-octyl phthalate; DINP = Diisononyl phthalate; DIDP = Diisodecyl phthalate ppm (Parts per million) = mg/kg (Milligrams per kilogram) = 0.0001 % w/w (Percent by weight) LT = Less than

ND = Not detected (Reporting Limit = 120ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.





Test Report #

Date of Issue:

Pages:



15H-01386

Page 4 of 8

April 10, 2015

# TEST REPORT

Company: Huffermen, Inc.

Recipient: Eric Miller

Recipient Email: eric@huffermen.com

cc to Email: - Date Received: March 26, 2015

### **DETAILED RESULTS:**

# FDA 21 CFR 177.1520, Polyethylene

Analysis performed by food simulating solvents extractions to determine compliance with above referenced regulation. [Referenced Test Method: FDA 21 CFR 177.1520]

Specime	1				
Test Item	Test Condition		Result	RL	Specification
rest item	Temperature	Duration	Result	KL	Specification
Density (g/cc)	NA NA		0.916	NA	0.85-1.00
n-Hexane extractive (% w/w)	50°C	2 hours	1.7	0.4	5.5
Xylene extractive (% w/w) Reflux 2 hours		3.1	1.0	11.3	
Conclu	PASS				

Specime	2				
Test Item	Test Condition		Result	RL	Cnocification
rest item	Temperature	Duration	Result	KL	Specification
Density (g/cc) NA NA		0.935	NA	0.85-1.00	
n-Hexane extractive (% w/w)	50°C	2 hours	0.7	0.4	5.5
Xylene extractive (% w/w)	Reflux	2 hours	1.4	1.0	11.3
Conclu	PASS				

### Note:

°C = Degree Celcius

g/cc = Grams per cubic centimeter

% w/w = Percent by weight

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

#### Remark:

The specification is quoted from 21 CFR 177.1520 (c) 2.1.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

# Test is not covered under ACLASS (Certificate # AT-1500) accredited listed scope.

ACLASS is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

ANSECO GROUP (HK) LIMITED 14/F, Yoo Hoo Tower, 38-42 Kwai Fung Crescent, Kwai Chung N.T., Hong Kong Tel: 852-3185 8000 Fax: 852-3572 0374







Company: Huffermen, Inc.

Recipient: Eric Miller

Recipient Email: eric@huffermen.com

cc to Email: -

Test Report # 15H-01386

Date of Issue: April 10, 2015

Pages: Page 5 of 8

Date Received: March 26, 2015

### **DETAILED RESULTS:**

# FDA 21 CFR 177.1520, Polyethylene

Analysis performed by food simulating solvents extractions to determine compliance with above referenced regulation. [Referenced Test Method: FDA 21 CFR 177.1520]

Specime	3				
Test Item	Test Condition		Result	RL	Specification
Test Helli	Temperature	Duration	Result	KL	Specification
Density (g/cc)	NA NA		0.918	NA	0.85-1.00
n-Hexane extractive (% w/w)	50°C	2 hours	0.4	0.4	5.5
Xylene extractive (% w/w) Reflux 2 hours		1.1	1.0	11.3	
Conclu	PASS				

#### Note:

°C = Degree Celcius

g/cc = Grams per cubic centimeter

% w/w = Percent by weight

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

#### Remark:

The specification is quoted from 21 CFR 177.1520 (c) 2.1.







Company: Huffermen, Inc.

Recipient: Eric Miller

Recipient Email: eric@huffermen.com

cc to Email: -

Test Report # 15H-01386

Date of Issue: April 10, 2015

Pages: Page 6 of 8

Date Received: March 26, 2015

#### **DETAILED RESULTS:**

# 16 CFR 1500, Federal Hazardous Substances Act (FHSA), Mechanical Hazards

Mechanical hazards evaluated as described in 16 CFR 1500.51-1500.53, as applicable.

Test	Conclusion	Observation
Impact	PASS	No Sharp Edges or Sharp Points
Torque	PASS	No Sharp Edges or Sharp Points
Tension	PASS	No Sharp Edges or Sharp Points
Compression	PASS	No Sharp Edges or Sharp Points

# 16 CFR 1500.3(c)(6)(vi), Flammability of Solids

Flammable hazards evaluated as described in 16 CFR 1500.44.

Test	Conclusion	Observation
Flammability of Solids	PASS	No Ignition. The content is not defined as flammable solid according to 16 CFR 1500.3(c)(6)(vi).







Company: Huffermen, Inc.

Recipient: Eric Miller

Recipient Email: eric@huffermen.com

cc to Email: -

Test Report # 15H-01386

Date of Issue: April 10, 2015

Pages: Page 7 of 8

Date Received: March 26, 2015

### SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
1	White plastic	Bottle (white small style)
2	Dull white plastic	Bottle (white large style)
3	Translucent plastic	Bottle (all styles)



Company: Huffermen, Inc.

Recipient: Eric Miller

Recipient Email: eric@huffermen.com

cc to Email: -





711 150

Test Report # 15H

15H-01386

Date of Issue:

April 10, 2015

Pages:

Page 8 of 8

Date Received:

March 26, 2015

### **SAMPLE PHOTO:**

CS-HK-RE005



-End Report-

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

# Test is not covered under ACLASS (Certificate # AT-1500) accredited listed scope.

ansecogroup.com