



TEST REPORT

Test Report # 18H-006110 Date of Report Issue: September 10, 2018
 Date of Sample Received: August 13, 2018 Pages: Page 1 of 43

CLIENT INFORMATION:

Company: Hit Promotional Products
 Recipient: Nathan Cotter
 Recipient Email: ncotter@hitpromo.net



18H-006110

SAMPLE INFORMATION:

Description:	16oz. Mug w/Lid	Purchase Order Number:	238273
Assortment:	7 colors	Agent:	Brand New Days
SKU No.:	8152	Country of Origin:	China
Factory No.:	106991	Labeled Age Grade:	-
Country of Distribution:	United States	Recommended Age Grade:	-
Quantity Submitted:	20 pcs (Red, Blue, Purple, Grey, Black), 19 pcs (Orange, Green) + 1 lot Parts	Tested Age Grade:	-
Testing Period:	08/20/2018 – 08/29/2018 09/05/2018 – 09/10/2018		

OVERALL RESULT:

PASS

Refer to page 2 for test result summary and appropriate notes.

ANSECO GROUP (HK) LIMITED

Loska Yeung Lok Ka
 Assistant Manager, Chemical Laboratory

ANSECO GROUP (HK) LIMITED ♦ 3/F Liven House ♦ No. 61 – 63 King Yip Street ♦ Kwun Tong ♦ Kowloon ♦ Hong Kong ♦ Tel: (852)3185 8000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

**TEST RESULTS SUMMARY:**

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	CPSIA Section 101, Total Lead in Substrate Materials
PASS	CPSIA Section 101, Total Lead in Glass and Ceramic Materials [#]
PASS	California Proposition 65, Total Lead in Substrate Materials
PASS	California Proposition 65, Total Lead in Glass and Ceramic Materials [#]
PASS	Client's Requirement, Bisphenol A and Bisphenol S [#]
PASS	FDA 21 CFR 177.1210, Closures with Sealing Gaskets [#]
PASS	FDA 21 CFR 177.1520, Polypropylene Copolymers
PASS	FDA 21 CFR 180.22 and 181.32, Acrylonitrile/Styrene Copolymers
PASS	California Proposition 65 Case No. 938430, Leachable Lead and Cadmium from Tableware (Shipment over 2,000 Pieces) – Interior
PASS	FDA CPG 545.400 & CPG 545.450, Leachable Cadmium and Lead from Ceramics – Interior
PASS	California Proposition 65 Case No. CGC-04-436729, Leachable Lead and Cadmium from Tableware – Lip and Rim
PASS	California Proposition 65 Case No. CGC-04-436429, Lead and Cadmium from Beverage Products – External Decoration [#]

**DETAILED RESULTS:****CPSIA Section 101, Total Lead in Substrate Materials**

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1	2+3	4+5+6	7+8	9	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

**DETAILED RESULTS:****CPSIA Section 101, Total Lead in Glass and Ceramic Materials**Test Method: In-House Method[#]

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	25	26	27	28	29	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	32	34	44	30	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	30	31	---	---	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	46	47	---	---	---	100
Conclusion	PASS	PASS	---	---	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.



DETAILED RESULTS:

California Proposition 65, Total Lead in Substrate Materials

Test Method: CPSC-CH-E1001-08.3 (Metal), CPSC-CH-E1002-08.3 (Non-Metal)
Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1	2+3	4+5+6	7+8	9	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	ND	ND	ND	ND	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client’s requirement.

**DETAILED RESULTS:****California Proposition 65, Total Lead in Glass and Ceramic Materials**Test Method: In-House Method[#]

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	25	26	27	28	29	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	32	34	44	30	ND	100
Conclusion	PASS	PASS	PASS	PASS	PASS	

Specimen No.	30	31	---	---	---	Total Limit (ppm)
Test Item	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	Result (ppm)	
Total Lead (Pb)	46	47	---	---	---	100
Conclusion	PASS	PASS	---	---	---	

Note:

ppm (Parts per million) = mg/kg (Milligrams per kilogram)

LT = Less than

ND = Not detected (Reporting Limit = 20 ppm)

Composite results are based on specimen of least mass resulting in highest potential concentration.

Remark:

The specification is quoted from client's requirement.

**DETAILED RESULTS:****Client's Requirement, Bisphenol A and Bisphenol S**

Test Method: In-House Method[#]
 Analytical Method: Liquid Chromatography with Mass Spectrometry

Specimen No.		1	2	3	4	Limit (ppb)
Test Item	CAS No.	Result (ppb)	Result (ppb)	Result (ppb)	Result (ppb)	
Bisphenol A (BPA)	80-05-7	ND	ND	ND	ND	ND
Bisphenol S (BPS)	80-09-1	ND	ND	ND	ND	ND
Conclusion		PASS	PASS	PASS	PASS	

Specimen No.		5	6	7	8	Limit (ppb)
Test Item	CAS No.	Result (ppb)	Result (ppb)	Result (ppb)	Result (ppb)	
Bisphenol A (BPA)	80-05-7	ND	ND	ND	ND	ND
Bisphenol S (BPS)	80-09-1	ND	ND	ND	ND	ND
Conclusion		PASS	PASS	PASS	PASS	

Specimen No.		9	---	---	---	Limit (ppb)
Test Item	CAS No.	Result (ppb)	Result (ppb)	Result (ppb)	Result (ppb)	
Bisphenol A (BPA)	80-05-7	ND	---	---	---	ND
Bisphenol S (BPS)	80-09-1	ND	---	---	---	ND
Conclusion		PASS	---	---	---	

Note:

ppb (Parts per billion) = µg/kg (Micrograms per kilogram)

NA = Not applicable

LT = Less than

ND = Not detected (Reporting limit: BPA = 1000 ppb; BPS = 200 ppb)



DETAILED RESULTS:

FDA 21 CFR 177.1210, Closures with Sealing Gaskets

Test Method: FDA 21 CFR 177.1210#

Specimen No.			9	---	RL	Limit
Test Item	Test Condition		Result (ppm)	Result (ppm)		
	Temp.	Duration				
Distilled water extractive	Fill boiling	Until Cool to 100°F	ND	---	10	50
Conclusion			PASS	---		

Note:

Temp. = Temperature

°F = Degree Fahrenheit

ppm (Parts per million) = mg/kg (Milligrams per kilogram foodstuff)

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1210 Table 2 Section 2.

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

**DETAILED RESULTS:****FDA 21 CFR 177.1520, Polypropylene Copolymers**

Test Method: FDA 21 CFR 177.1520

Specimen No.			2	3	RL	Limit
Test Item	Temp.	Duration	Result	Result		
Density (g/cc)	NA	NA	0.893	0.893	NA	0.85-1.00
n-Hexane extractive (%)	50°C	2 hours	1.2	1.2	0.4	5.5
Xylene extractive (%)	Reflux	2 hours or until total dissolved	3.5	4.2	1.0	30
Conclusion			PASS	PASS		

Specimen No.			4	5	RL	Limit
Test Item	Temp.	Duration	Result	Result		
Density (g/cc)	NA	NA	0.894	0.897	NA	0.85-1.00
n-Hexane extractive (%)	50°C	2 hours	1.4	1.3	0.4	5.5
Xylene extractive (%)	Reflux	2 hours or until total dissolved	3.5	3.4	1.0	30
Conclusion			PASS	PASS		

Note:

Temp. = Temperature

°C = Degree Celsius

g/cc = Grams per cubic centimeter

% = Percent by weight

NA = Not applicable

LT = Less than

ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1520 (c) 3.1a.



DETAILED RESULTS:

FDA 21 CFR 177.1520, Polypropylene Copolymers

Test Method: FDA 21 CFR 177.1520

Specimen No.			6	7	RL	Limit
Test Item	Temp.	Duration	Result	Result		
Density (g/cc)	NA	NA	0.895	0.891	NA	0.85-1.00
n-Hexane extractive (%)	50°C	2 hours	1.6	1.8	0.4	5.5
Xylene extractive (%)	Reflux	2 hours or until total dissolved	4.4	4.6	1.0	30
Conclusion			PASS	PASS		

Specimen No.			8	---	RL	Limit
Test Item	Temp.	Duration	Result	Result		
Density (g/cc)	NA	NA	0.892	---	NA	0.85-1.00
n-Hexane extractive (%)	50°C	2 hours	0.8	---	0.4	5.5
Xylene extractive (%)	Reflux	2 hours or until total dissolved	2.3	---	1.0	30
Conclusion			PASS	---		

Note:

- Temp. = Temperature
- °C = Degree Celsius
- g/cc = Grams per cubic centimeter
- % = Percent by weight
- NA = Not applicable
- LT = Less than
- ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 177.1520 (c) 3.1a.

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



DETAILED RESULTS:

FDA 21 CFR 180.22 and 181.32, Acrylonitrile/Styrene Copolymers

Test Method: FDA 21 CFR 180.22 and 181.32
Analytical Method: Headspace-Gas Chromatography with Mass Spectrometry

Acrylonitrile Monomers:

Specimen No.			1	RL	Limit
Test Simulant	Test Condition		Result		
	Temp.	Duration			
Distilled water extractive (mg/in ²)	120°F	2 hours	ND	0.001	0.003
3% Acetic acid extractive (mg/in ²)	120°F	2 hours	ND	0.001	0.003
Conclusion			PASS		

Note:

Temp. = Temperature
°F = Degree Fahrenheit
mg/in² = Milligrams per square inch
LT = Less than
ND = Not detected. Result value is less than reporting limit (RL).

Remark:

The specification is quoted from 21 CFR 181.32 (b) (3).

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein. This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited. ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

**DETAILED RESULTS:****California Proposition 65 Case No. 938430, Leachable Lead and Cadmium from Tableware (Shipment over 2,000 Pieces) – Interior**

Test Method: ASTM C738-94(Reapproved 2011)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	10A	10B	10C	10D	10E	10F	10G
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)
Volume of acid used (mL)	430	430	430	430	430	430	430
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	ND
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	ND
Conclusion							

Specimen No.	10H	10I	10J	10K	10L	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	430	430	430	430	430		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	0.049
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	0.100
Conclusion						PASS	

Note:

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

NA = Not applicable

LT = Less than

ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)



	Category	Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Average of 12)	0.049	0.100
	Flatware (Average of 12)	0.189	0.226
	Large Hollowware (Average of 12)	0.049	0.100
	Small Hollowware (Average of 12)	0.049	0.100
	Pitchers (Average of 12)	0.049	0.100

**DETAILED RESULTS:****California Proposition 65 Case No. 938430, Leachable Lead and Cadmium from Tableware (Shipment over 2,000 Pieces) – Interior**

Test Method: ASTM C738-94(Reapproved 2011)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	11A	11B	11C	11D	11E	11F	11G
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)
Volume of acid used (mL)	430	430	430	430	430	430	430
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	ND
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	ND
Conclusion							

Specimen No.	11H	11I	11J	11K	11L	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	430	430	430	430	430		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	0.049
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	0.100
Conclusion						PASS	

Note:

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

NA = Not applicable

LT = Less than

ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)



	Category	Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Average of 12)	0.049	0.100
	Flatware (Average of 12)	0.189	0.226
	Large Hollowware (Average of 12)	0.049	0.100
	Small Hollowware (Average of 12)	0.049	0.100
	Pitchers (Average of 12)	0.049	0.100

**DETAILED RESULTS:****California Proposition 65 Case No. 938430, Leachable Lead and Cadmium from Tableware (Shipment over 2,000 Pieces) – Interior**

Test Method: ASTM C738-94(Reapproved 2011)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	12A	12B	12C	12D	12E	12F	12G
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)
Volume of acid used (mL)	430	430	430	430	430	430	430
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	ND
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	ND
Conclusion							

Specimen No.	12H	12I	12J	12K	12L	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	430	430	430	430	430		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	0.049
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	0.100
Conclusion						PASS	

Note:

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

NA = Not applicable

LT = Less than

ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)



Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Average of 12)	0.049	0.100
	Flatware (Average of 12)	0.189	0.226
	Large Hollowware (Average of 12)	0.049	0.100
	Small Hollowware (Average of 12)	0.049	0.100
	Pitchers (Average of 12)	0.049	0.100

**DETAILED RESULTS:****California Proposition 65 Case No. 938430, Leachable Lead and Cadmium from Tableware (Shipment over 2,000 Pieces) – Interior**

Test Method: ASTM C738-94(Reapproved 2011)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	13A	13B	13C	13D	13E	13F	13G
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)
Volume of acid used (mL)	430	430	430	430	430	430	430
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	ND
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	ND
Conclusion							

Specimen No.	13H	13I	13J	13K	13L	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	430	430	430	430	430		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	0.049
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	0.100
Conclusion						PASS	

Note:

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

NA = Not applicable

LT = Less than

ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)



Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Average of 12)	0.049	0.100
	Flatware (Average of 12)	0.189	0.226
	Large Hollowware (Average of 12)	0.049	0.100
	Small Hollowware (Average of 12)	0.049	0.100
	Pitchers (Average of 12)	0.049	0.100

**DETAILED RESULTS:****California Proposition 65 Case No. 938430, Leachable Lead and Cadmium from Tableware (Shipment over 2,000 Pieces) – Interior**

Test Method: ASTM C738-94(Reapproved 2011)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	14A	14B	14C	14D	14E	14F	14G
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)
Volume of acid used (mL)	430	430	430	430	430	430	430
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	ND
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	ND
Conclusion							

Specimen No.	14H	14I	14J	14K	14L	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	430	430	430	430	430		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	0.049
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	0.100
Conclusion						PASS	

Note:

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

NA = Not applicable

LT = Less than

ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)



Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Average of 12)	0.049	0.100
	Flatware (Average of 12)	0.189	0.226
	Large Hollowware (Average of 12)	0.049	0.100
	Small Hollowware (Average of 12)	0.049	0.100
	Pitchers (Average of 12)	0.049	0.100

**DETAILED RESULTS:****California Proposition 65 Case No. 938430, Leachable Lead and Cadmium from Tableware (Shipment over 2,000 Pieces) – Interior**

Test Method: ASTM C738-94(Reapproved 2011)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	15A	15B	15C	15D	15E	15F	15G
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)
Volume of acid used (mL)	430	430	430	430	430	430	430
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	ND
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	ND
Conclusion							

Specimen No.	15H	15I	15J	15K	15L	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	430	430	430	430	430		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	0.049
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	0.100
Conclusion						PASS	

Note:

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

NA = Not applicable

LT = Less than

ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)



	Category	Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Average of 12)	0.049	0.100
	Flatware (Average of 12)	0.189	0.226
	Large Hollowware (Average of 12)	0.049	0.100
	Small Hollowware (Average of 12)	0.049	0.100
	Pitchers (Average of 12)	0.049	0.100

**DETAILED RESULTS:****California Proposition 65 Case No. 938430, Leachable Lead and Cadmium from Tableware (Shipment over 2,000 Pieces) – Interior**

Test Method: ASTM C738-94(Reapproved 2011)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	16A	16B	16C	16D	16E	16F	16G
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)
Volume of acid used (mL)	430	430	430	430	430	430	430
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	ND
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	ND
Conclusion							

Specimen No.	16H	16I	16J	16K	16L	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	430	430	430	430	430		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	0.049
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	0.100
Conclusion						PASS	

Note:

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

NA = Not applicable

LT = Less than

ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)



Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Average of 12)	0.049	0.100
	Flatware (Average of 12)	0.189	0.226
	Large Hollowware (Average of 12)	0.049	0.100
	Small Hollowware (Average of 12)	0.049	0.100
	Pitchers (Average of 12)	0.049	0.100

**DETAILED RESULTS:****FDA CPG 545.400 & CPG 545.450, Leachable Cadmium and Lead from Ceramics – Interior**

Test Method: ASTM C738-94(Reapproved 2011)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	10A	10B	10C	10D	10E	10F	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	430	430	430	430	430	430		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	NA	0.5
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	NA	0.5
Conclusion	PASS	PASS	PASS	PASS	PASS	PASS		

Note:

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

NA = Not applicable

LT = Less than

ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Any of 6)	0.5	0.5
	Flatware (Average of 6)	0.5	3.0
	Large Hollowware (Any of 6)	0.25	1.0
	Small Hollowware (Any of 6)	0.5	2.0
	Pitchers (Any of 6)	0.25	0.5

**DETAILED RESULTS:****FDA CPG 545.400 & CPG 545.450, Leachable Cadmium and Lead from Ceramics – Interior**

Test Method: ASTM C738-94(Reapproved 2011)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	11A	11B	11C	11D	11E	11F	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	430	430	430	430	430	430		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	NA	0.5
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	NA	0.5
Conclusion	PASS	PASS	PASS	PASS	PASS	PASS		

Note:

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

NA = Not applicable

LT = Less than

ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Any of 6)	0.5	0.5
	Flatware (Average of 6)	0.5	3.0
	Large Hollowware (Any of 6)	0.25	1.0
	Small Hollowware (Any of 6)	0.5	2.0
	Pitchers (Any of 6)	0.25	0.5

**DETAILED RESULTS:****FDA CPG 545.400 & CPG 545.450, Leachable Cadmium and Lead from Ceramics – Interior**

Test Method: ASTM C738-94(Reapproved 2011)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	12A	12B	12C	12D	12E	12F	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	430	430	430	430	430	430		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	NA	0.5
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	NA	0.5
Conclusion	PASS	PASS	PASS	PASS	PASS	PASS		

Note:

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

NA = Not applicable

LT = Less than

ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Any of 6)	0.5	0.5
	Flatware (Average of 6)	0.5	3.0
	Large Hollowware (Any of 6)	0.25	1.0
	Small Hollowware (Any of 6)	0.5	2.0
	Pitchers (Any of 6)	0.25	0.5

**DETAILED RESULTS:****FDA CPG 545.400 & CPG 545.450, Leachable Cadmium and Lead from Ceramics – Interior**

Test Method: ASTM C738-94(Reapproved 2011)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	13A	13B	13C	13D	13E	13F	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	430	430	430	430	430	430		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	NA	0.5
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	NA	0.5
Conclusion	PASS	PASS	PASS	PASS	PASS	PASS		

Note:

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

NA = Not applicable

LT = Less than

ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Any of 6)	0.5	0.5
	Flatware (Average of 6)	0.5	3.0
	Large Hollowware (Any of 6)	0.25	1.0
	Small Hollowware (Any of 6)	0.5	2.0
	Pitchers (Any of 6)	0.25	0.5

**DETAILED RESULTS:****FDA CPG 545.400 & CPG 545.450, Leachable Cadmium and Lead from Ceramics – Interior**

Test Method: ASTM C738-94(Reapproved 2011)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	14A	14B	14C	14D	14E	14F	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	430	430	430	430	430	430		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	NA	0.5
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	NA	0.5
Conclusion	PASS	PASS	PASS	PASS	PASS	PASS		

Note:

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

NA = Not applicable

LT = Less than

ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Any of 6)	0.5	0.5
	Flatware (Average of 6)	0.5	3.0
	Large Hollowware (Any of 6)	0.25	1.0
	Small Hollowware (Any of 6)	0.5	2.0
	Pitchers (Any of 6)	0.25	0.5



DETAILED RESULTS:

FDA CPG 545.400 & CPG 545.450, Leachable Cadmium and Lead from Ceramics – Interior

Test Method: ASTM C738-94(Reapproved 2011)
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	15A	15B	15C	15D	15E	15F	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	430	430	430	430	430	430		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	NA	0.5
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	NA	0.5
Conclusion	PASS	PASS	PASS	PASS	PASS	PASS		

Note:

mL = Millilitres
 mg/L (Milligrams per litre) = ppm (Parts per million)
 NA = Not applicable
 LT = Less than
 ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Any of 6)	0.5	0.5
	Flatware (Average of 6)	0.5	3.0
	Large Hollowware (Any of 6)	0.25	1.0
	Small Hollowware (Any of 6)	0.5	2.0
	Pitchers (Any of 6)	0.25	0.5

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein. This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited. ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.



DETAILED RESULTS:

FDA CPG 545.400 & CPG 545.450, Leachable Cadmium and Lead from Ceramics – Interior

Test Method: ASTM C738-94(Reapproved 2011)
 Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	16A	16B	16C	16D	16E	16F	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of acid used (mL)	430	430	430	430	430	430		
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	NA	0.5
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	NA	0.5
Conclusion	PASS	PASS	PASS	PASS	PASS	PASS		

Note:

mL = Millilitres
 mg/L (Milligrams per litre) = ppm (Parts per million)
 NA = Not applicable
 LT = Less than
 ND = Not detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

Category		Leachable Cd (mg/L)	Leachable Pb (mg/L)
X	Cups and Mugs (Any of 6)	0.5	0.5
	Flatware (Average of 6)	0.5	3.0
	Large Hollowware (Any of 6)	0.25	1.0
	Small Hollowware (Any of 6)	0.5	2.0
	Pitchers (Any of 6)	0.25	0.5

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation. The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein. This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited. ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

**DETAILED RESULTS:****California Proposition 65 Case No. CGC-04-436729, Leachable Lead and Cadmium from Tableware – Lip and Rim**

Test Method: ASTM C927-80(2014)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	17A	17B	17C	17D	17E	17F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	180	180	180	180	180	180	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	2.0
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	0.5
Conclusion	PASS	PASS	PASS	PASS	PASS	PASS	

Note:

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

LT = Less than

ND = Not Detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

**DETAILED RESULTS:****California Proposition 65 Case No. CGC-04-436729, Leachable Lead and Cadmium from Tableware – Lip and Rim**

Test Method: ASTM C927-80(2014)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	18A	18B	18C	18D	18E	18F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	180	180	180	180	180	180	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	2.0
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	0.5
Conclusion	PASS	PASS	PASS	PASS	PASS	PASS	

Note:

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

LT = Less than

ND = Not Detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

**DETAILED RESULTS:****California Proposition 65 Case No. CGC-04-436729, Leachable Lead and Cadmium from Tableware – Lip and Rim**

Test Method: ASTM C927-80(2014)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	19A	19B	19C	19D	19E	19F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	180	180	180	180	180	180	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	2.0
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	0.5
Conclusion	PASS	PASS	PASS	PASS	PASS	PASS	

Note:

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

LT = Less than

ND = Not Detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

**DETAILED RESULTS:****California Proposition 65 Case No. CGC-04-436729, Leachable Lead and Cadmium from Tableware – Lip and Rim**

Test Method: ASTM C927-80(2014)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	20A	20B	20C	20D	20E	20F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	180	180	180	180	180	180	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	2.0
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	0.5
Conclusion	PASS	PASS	PASS	PASS	PASS	PASS	

Note:

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

LT = Less than

ND = Not Detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

**DETAILED RESULTS:****California Proposition 65 Case No. CGC-04-436729, Leachable Lead and Cadmium from Tableware – Lip and Rim**

Test Method: ASTM C927-80(2014)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	21A	21B	21C	21D	21E	21F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	180	180	180	180	180	180	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	2.0
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	0.5
Conclusion	PASS	PASS	PASS	PASS	PASS	PASS	

Note:

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

LT = Less than

ND = Not Detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

**DETAILED RESULTS:****California Proposition 65 Case No. CGC-04-436729, Leachable Lead and Cadmium from Tableware – Lip and Rim**

Test Method: ASTM C927-80(2014)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	22A	22B	22C	22D	22E	22F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	180	180	180	180	180	180	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	2.0
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	0.5
Conclusion	PASS	PASS	PASS	PASS	PASS	PASS	

Note:

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

LT = Less than

ND = Not Detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)

**DETAILED RESULTS:****California Proposition 65 Case No. CGC-04-436729, Leachable Lead and Cadmium from Tableware – Lip and Rim**

Test Method: ASTM C927-80(2014)

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	23A	23B	23C	23D	23E	23F	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)	
Volume of acid used (mL)	180	180	180	180	180	180	
Leachable Cadmium (Cd)	ND	ND	ND	ND	ND	ND	2.0
Leachable Lead (Pb)	ND	ND	ND	ND	ND	ND	0.5
Conclusion	PASS	PASS	PASS	PASS	PASS	PASS	

Note:

mL = Millilitres

mg/L (Milligrams per litre) = ppm (Parts per million)

LT = Less than

ND = Not Detected (Reporting Limit: Pb = 0.04 mg/L; Cd = 0.02 mg/L)



DETAILED RESULTS:

California Proposition 65 Case No. CGC-04-436429, Lead and Cadmium from Beverage Products – External Decoration

Test Method: NIOSH Method 9100#

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	24	---	---	---	---	Limit (µg/article)
Test Item	Result (µg/article)	Result (µg/article)	Result (µg/article)	Result (µg/article)	Result (µg/article)	
Cadmium (Cd)	ND	---	---	---	---	1.0
Lead (Pb)	ND	---	---	---	---	1.0
Conclusion	PASS	---	---	---	---	

Note:

µg/article = Micrograms per article

LT = Less than

ND = Not detected (Reporting Limit = 0.4 µg/article)

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

**SPECIMEN DESCRIPTION:**

Specimen No.	Specimen Description	Location
1	Clear plastic (AS)	Lid (all styles)
2	Red plastic (PP-co)	Slider (red style)
3	Orange plastic (PP-co)	Slider (orange style)
4	Green plastic (PP-co)	Slider (green style)
5	Blue plastic (PP-co)	Slider (blue style)
6	Purple plastic (PP-co)	Slider (purple style)
7	Grey plastic (PP-co)	Slider (grey style)
8	Black plastic (PP-co)	Slider (black style)
9	Translucent soft plastic (Silicone)	Gasket (all styles)
10	Red printed dull white ceramic	Interior of mug (red style)
11	Orange printed dull white ceramic	Interior of mug (orange style)
12	Green printed dull white ceramic	Interior of mug (green style)
13	Blue printed dull white ceramic	Interior of mug (blue style)
14	Purple printed dull white ceramic	Interior of mug (purple style)
15	Grey printed dull white ceramic	Interior of mug (grey style)
16	Black printed dull white ceramic	Interior of mug (black style)
17	Red/ white printed dull white ceramic	Lip & Rim of mug (red style)
18	Orange/ white printed dull white ceramic	Lip & Rim of mug (orange style)
19	Green/ white printed dull white ceramic	Lip & Rim of mug (green style)
20	Blue/ white printed dull white ceramic	Lip & Rim of mug (blue style)

**SPECIMEN DESCRIPTION:**

Specimen No.	Specimen Description	Location
21	Purple/ white printed dull white ceramic	Lip & Rim of mug (purple style)
22	Grey/ white printed dull white ceramic	Lip & Rim of mug (grey style)
23	Black/ white printed dull white ceramic	Lip & Rim of mug (black style)
24	White printed dull white ceramic	External decoration of mug (all styles)
25	Red/ white printed dull white ceramic	Whole of mug (red style)
26	Orange/ white printed dull white ceramic	Whole of mug (orange style)
27	Green/ white printed dull white ceramic	Whole of mug (green style)
28	Blue/ white printed dull white ceramic	Whole of mug (blue style)
29	Purple/ white printed dull white ceramic	Whole of mug (purple style)
30	Grey/ white printed dull white ceramic	Whole of mug (grey style)
31	Black/ white printed dull white ceramic	Whole of mug (black style)



Test Report #

18H-006110

Pages:

Page 43 of 43

SAMPLE PHOTO:



-End Report-

ANSECO GROUP (HK) LIMITED ♦ 3/F Liven House ♦ No. 61 – 63 King Yip Street ♦ Kwun Tong ♦ Kowloon ♦ Hong Kong ♦ Tel: (852)3185 8000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.